IEEE Std C57.106™-2002
(Revision of
IEEE Std C57.106-1991)

IEEE Standards

C57.106™

IEEE Guide for Acceptance and Maintenance of Insulating Oil in Equipment

IEEE Power Engineering Society

Sponsored by the
Transformers Committee

IEEE

Published by
The Institute of Electrical and Electronics Engineers, Inc.
3 Park Avenue, New York, NY 10016-5997, USA

8 November 2002

Print: SH95008
PDF: SS95008

--`,,-`-`,,`,,`,`,,`---

Copyright The Institute of Electrical and Electronics Engineers, Inc.
Provided by IHS under license with IEEE
No reproduction or networking permitted without license from IHS

Not for Resale

Recognized as an
American National Standard (ANSI)

IEEE Std C57.106™-2002
(Revision of
IEEE Std C57.106-1991)

IEEE Guide for Acceptance and Maintenance of Insulating Oil Equipment

Sponsor

Transformers Committee
of the
IEEE Power Engineering Society

Approved 30 October 2002

American National Standards Institute

Approved 13 June 2002

IEEE-SA Standards Board

Abstract: Recommendations regarding oil tests and evaluation procedures are made in this guide; references are made to methods of reconditioning and reclaiming conventional petroleum (mineral) dielectric insulating oils; the levels at which these methods become necessary; and the routines for restoring oxidation resistance, where required, by the addition of oxidation inhibitors. The intent is to assist the power equipment operator in evaluating the serviceability of oil received in equipment, oil as received from the supplier for filling new equipment at the installation site, and oil as processed into such equipment; and to assist the operator in maintaining oil in serviceable condition. The mineral oil covered is used in transformers, reactors, circuit breakers, load tap changers, and voltage regulators.
Keywords: insulation testing, load tap changers, oil circuit breakers, oil insulation, power distribution maintenance, power transformer insulation, reactors, transformers, voltage regulators

---

The Institute of Electrical and Electronics Engineers, Inc.
3 Park Avenue, New York, NY 10016-5997, USA

Copyright © 2002 by the Institute of Electrical and Electronics Engineers, Inc.
All rights reserved. Published 8 November 2002. Printed in the United States of America.

Print: ISBN 0-7381-3319-1 SH95008
PDF: ISBN 0-7381-3320-5 SS95008

No part of this publication may be reproduced in any form, in an electronic retrieval system or otherwise, without the prior written permission of the publisher.

Copyright The Institute of Electrical and Electronics Engineers, Inc.
Provided by IHS under license with IEEE
No reproduction or networking permitted without license from IHS
Not for Resale

IEEE Standards documents are developed within the IEEE Societies and the Standards Coordinating Committees of the IEEE Standards Association (IEEE-SA) Standards Board. The IEEE develops its standards through a consensus development process, approved by the American National Standards Institute, which brings together volunteers representing varied viewpoints and interests to achieve the final product. Volunteers are not necessarily members of the Institute and serve without compensation. While the IEEE administers the process and establishes rules to promote fairness in the consensus development process, the IEEE does not independently evaluate, test, or verify the accuracy of any of the information contained in its standards.

Use of an IEEE Standard is wholly voluntary. The IEEE disclaims liability for any personal injury, property or other damage, of any nature whatsoever, whether special, indirect, consequential, or compensatory, directly or indirectly resulting from the publication, use of, or reliance upon this, or any other IEEE Standard document.

The IEEE does not warrant or represent the accuracy or content of the material contained herein, and expressly disclaims any express or implied warranty, including any implied warranty of merchantability or fitness for a specific purpose, or that the use of the material contained herein is free from patent infringement. IEEE Standards documents are supplied "**AS IS**."

The existence of an IEEE Standard does not imply that there are no other ways to produce, test, measure, purchase, market, or provide other goods and services related to the scope of the IEEE Standard. Furthermore, the viewpoint expressed at the time a standard is approved and issued is subject to change brought about through developments in the state of the art and comments received from users of the standard. Every IEEE Standard is subjected to review at least every five years for revision or reaffirmation. When a document is more than five years old and has not been reaffirmed, it is reasonable to conclude that its contents, although still of some value, do not wholly reflect the present state of the art. Users are cautioned to check to determine that they have the latest edition of any IEEE Standard.

In publishing and making this document available, the IEEE is not suggesting or rendering professional or other services for, or on behalf of, any person or entity. Nor is the IEEE undertaking to perform any duty owed by any other person or entity to another. Any person utilizing this, and any other IEEE Standards document, should rely upon the advice of a competent professional in determining the exercise of reasonable care in any given circumstances.

Interpretations: Occasionally questions may arise regarding the meaning of portions of standards as they relate to specific applications. When the need for interpretations is brought to the attention of IEEE, the Institute will initiate action to prepare appropriate responses. Since IEEE Standards represent a consensus of concerned interests, it is important to ensure that any interpretation has also received the concurrence of a balance of interests. For this reason, IEEE and the members of its societies and Standards Coordinating Committees are not able to provide an instant response to interpretation requests except in those cases where the matter has previously received formal consideration.

Comments for revision of IEEE Standards are welcome from any interested party, regardless of membership affiliation with IEEE. Suggestions for changes in documents should be in the form of a proposed change of text, together with appropriate supporting comments. Comments on standards and requests for interpretations should be addressed to:

Secretary, IEEE-SA Standards Board
445 Hoes Lane
P.O. Box 1331
Piscataway, NJ 08855-1331
USA

Note: Attention is called to the possibility that implementation of this standard may require use of subject matter covered by patent rights. By publication of this standard, no position is taken with respect to the existence or validity of any patent rights in connection therewith. The IEEE shall not be responsible for identifying patents for which a license may be required by an IEEE standard or for conducting inquiries into the legal validity or scope of those patents that are brought to its attention.

Authorization to photocopy portions of any individual standard for internal or personal use is granted by the Institute of Electrical and Electronics Engineers, Inc., provided that the appropriate fee is paid to Copyright Clearance Center. To arrange for payment of licensing fee, please contact Copyright Clearance Center, Customer Service, 222 Rosewood Drive, Danvers, MA 01923 USA; +1 978 750 8400. Permission to photocopy portions of any individual standard for educational classroom use can also be obtained through the Copyright Clearance Center.

--`,,`-`-`,,`,,`,`,,`---

Copyright The Institute of Electrical and Electronics Engineers, Inc.
Provided by IHS under license with IEEE
No reproduction or networking permitted without license from IHS

Not for Resale

Introduction

(This introduction is not part of IEEE Std C57.106-2002, IEEE Guide for Acceptance and Maintenance of Insulating Oil in Equipment.)

Participants

At the time this document went to ballot, the Accredited Standards Committee on Transformers, Regulators, and Reactors, C57, had the following members:

J. D. Borst, *Chair*
D. J. Rolling, *Vice-Chair*
J. A. Gauthier, *Secretary*

Glenn Anderson
G. Coulter
F. Elliott
Mehrdad Eskandary
Peyton E. Glenn
P. Hall
K. S. Hanus
P. Hopkinson
Mary R. Jordan
S. Kennedy
F. Lewis
Boyd Luenberger
J. W. Matthews
G. Morehart
R. Nichols
Carl G. Niemann
B. Patel
Alan D. Peterson
Tom A. Prevost
Hyeong Jin Sim
H. Smith
J. Sullivan
Kenneth C. Wolohan

This guide was prepared by the Insulating Fluids Subcommittee of the Transformers Committee of the IEEE Power Engineering Society. At the time this guide was completed, the working group had the following membership:

J. J. Kelly, *Chair*
S. J. McNelly, *Technical Editor*

P. Balma
F. J. Gryszkiewicz
T. J. Haupert
F. Heinrichs
M. E. Horning
F. Jakob
E. Kallaur
J. G. Lackey
R. Ladroga
M. Y. Lau
T. Lundquist
P. McShane
H. R. Moore
T. V. Oommen
C. T. Raymond
G. J. Reitter
J. E. Smith
J. A. Thompson
T. P. Traub

Copyright © 2002 IEEE. All rights reserved.

Copyright The Institute of Electrical and Electronics Engineers, Inc.
Provided by IHS under license with IEEE
No reproduction or networking permitted without license from IHS
Not for Resale

The following members of the balloting committee voted on this standard. Balloters may have voted for approval, disapproval, or abstention.

Mario Aguirre
Paul Ahrens
Raymond Allustiarti
William A. Andersen
Jim Antweiler
Jacques Aubin
P. Balma
Ralph Barker
C. M. Bartley
Martin A. Baur
Barry L. Beaster
Edward A. Bertolini
Enrique Betancourt
Thomas E. Blackburn III
William E. Boettger
Broady Cash
Robert C. Degeneff
Guru Dutt Dhingra
Dieter Dohnal
Charles J. Elliott
Alexander E. Emanuel
Jorge Fernandez-Daher
Michael A. Franchek
Dudley L. Galloway
Jorge Garcia
George Gela
Donald A. Gillies
Lawrence T. Groves
Robert L. Grunert
F. J. Gryszkiewicz
Heine Hansen
Justin Harlow
Robert H. Hartgrove
James W. Hayes
F. Heinrichs
William R. Henning
Keith R. Highton
Scott Hopkinson
Richard Horning
James D. Huddleston, III
J. Hughes
Robert W. Ingham
Katee James
Larry Kelly
Michael Kennedy
Brian Klaponski
William Lackey
Terry Lambert
William E. Larzelere
K. B. Lau
Maurice Linker
R. Lowe
Mark Lundquist
Gregory Luri
Catherine Ma
Lee Maguire
K. T. Massouda
Lee Matthews
Massimo Mattiuzzo
S. J. McNelly
Ross McTaggart
Israel Michel
Melvin Miller
H. R. Moore
O. W. Mulkey
Richard J. Musil
Ernest H. Neubauer
T. V. Oommen
Narenda Patel
R. Patton
D. W. Payne
Carlos O. Peixoto
J. F. Perkins
Michael Pierce
R. Leon Plaster
J. E. Platts
G. Preininger
Tom A. Prevost
E Purra
Madan Rana
G. J. Reitter
John R. Rossetti
A. E. Rouse
James A. Ruggieri
Ravi Sankar
D. Sawyer
Michael Scully
Sat P. Sharma
Hyeong Jin Sim
Ralph E. Snyder
Brian Sparling
Ronald J. Stahara
J. R. Stevens
Ron W. Stoner
Richard E. Sullivan
Lance Thompson
Michael K. Toney
T. P. Traub
Subhash C. Tuli
John Vandermaar
Joseph J. Vaschak
Michael W. Vaughn
Steve Watson
Robert Whearty
A. Wilks
Donald L. Wilson
William G. Wimmer

When the IEEE-SA Standards Board approved this standard on 13 June 2002, it had the following membership:

James T. Carlo, *Chair*

James H. Gurney, *Vice Chair*

Judith Gorman, *Secretary*

Sid Bennett
H. Stephen Berger
Clyde R. Camp
Richard DeBlasio
Harold E. Epstein
Julian Forster*
Howard M. Frazier
Toshio Fukuda
Arnold M. Greenspan
Raymond Hapeman
Donald M. Heirman
Richard H. Hulett
Lowell G. Johnson
Joseph L. Koepfinger*
Peter H. Lips
Nader Mehravari
Daleep C. Mohla
William J. Moylan
Malcolm V. Thaden
Geoffrey O. Thompson
Howard L. Wolfman
Don Wright

*Member Emeritus

Copyright © 2002 IEEE. All rights reserved.

Copyright The Institute of Electrical and Electronics Engineers, Inc.
Provided by IHS under license with IEEE
No reproduction or networking permitted without license from IHS
Not for Resale

Also included are the following nonvoting IEEE-SA Standards Board liaisons:

Alan Cookson, *NIST Representative*
Satish K. Aggarwal, *NRC Representative*

Andrew Ickowicz
IEEE Standards Project Editor

Copyright © 2002 IEEE. All rights reserved.

--`,,`-`-`,,`,,`,`,,`---

Copyright The Institute of Electrical and Electronics Engineers, Inc.
Provided by IHS under license with IEEE
No reproduction or networking permitted without license from IHS

Not for Resale

Contents

1. Overview 1

1.1 Scope 1
1.2 Purpose 2

2. References 2

3. Definitions 4

4. Evaluation of mineral insulating oil 4

4.1 General 4
4.2 New oil properties 5
4.3 New oil properties—oil received in new equipment rated less than 230 kV 6
4.4 New oil properties—after filling into new equipment rated at 230 kV or higher 7
4.5 Percent saturation of water in mineral oil (see also clause on saturation of water in oil in IEEE Std 62-1995 8
4.6 Mixtures of mineral insulating oil 10
4.7 Sampling 11

5. Oil tests and their significance 11

5.1 Physical tests 12
5.2 Electrical tests 13
5.3 Chemical tests 15

6. Handling and storage 16

6.1 Tanks 17
6.2 Oil quality protection in storage 17
6.3 Dikes and curbs 17
6.4 Processing oil for installation in apparatus 17

7. Classification of service-aged insulating oil 18

7.1 General 18
7.2 Classification 18

8. Insulating oil for circuit breakers 19

8.1 General 19
8.2 Testing 20
8.3 Reconditioning 23

9. Insulating oil for load tap changers (LTCs) 23

9.1 General 23
9.2 Testing methods 24
9.3 Reconditioning 24

10. Health and environmental care procedures for mineral insulating oil 25

10.1 Health issues 25
10.2 Leaks and spills 26

Annex A (informative) Bibliography 27

--`,,`,,`-`-`,,`,,`,`,,`---

Copyright © 2002 IEEE. All rights reserved.

Copyright The Institute of Electrical and Electronics Engineers, Inc.
Provided by IHS under license with IEEE
No reproduction or networking permitted without license from IHS

Not for Resale

IEEE Guide for Acceptance and Maintenance of Insulating Oil in Equipment

1. Overview

The reliable performance of oil in insulation systems depends upon basic characteristics of the oil that can affect overall apparatus characteristics. These oil characteristics are integral parts of the equipment design of the manufacturer. Certain properties of mineral insulating oil have been determined as important for proper electrical equipment performance. Description of these properties and their recommended value ranges for new oil and for continued use of service-aged oils are included in this guide.

Mineral insulating oil that is received in electrical equipment will exhibit different characteristics from new oil received in bulk, which has not been in contact with apparatus construction materials.

Oil in service may contain dissolved gases that are useful in assessing the continued serviceability of certain types of transformers. It is not the intent of this guide to cover this subject, as that information is available in IEEE C57.104™-1991[1].

This guide reflects the current state of the art and may differ from information contained in IEEE Std 62™-1995, which was authored by the Power System Instrumentation and Measurements (PSIM) Committee.

Should instructions or product standards given by the manufacturer differ from recommendations made in this guide, the instructions of the manufacturer are to be given preference.

1.1 Scope

This guide applies to mineral oil used in transformers, load tap changers, voltage regulators, reactors, and circuit breakers. The guide discusses the following:

a) Analytical tests and their significance for the evaluation of mineral insulating oil.
b) The evaluation of new, unused mineral insulating oil before and after filling into equipment.
c) Methods of handling and storage of mineral insulating oil.
d) The evaluation of service-aged mineral insulating oil.
e) Health and environmental care procedures for mineral insulating oil.

[1]Information on references can be found in Clause 2.

Copyright © 2002 IEEE. All rights reserved.

--`,,`-`-`,,`,,`,`,,`---
Copyright The Institute of Electrical and Electronics Engineers, Inc.
Provided by IHS under license with IEEE
No reproduction or networking permitted without license from IHS
Not for Resale

The characteristics of the oils discussed in this guide do not include oil that is in factory fill lines, nor does this guide cover reclaimed oil installed in new equipment. The qualities of such oil, if used, should be agreed upon by the manufacturer and the user of the equipment.

1.2 Purpose

The purpose of this guide is to assist the user of the equipment in evaluating the serviceability of new, unused oil being received in equipment; oil as received for filling new equipment at the installation site; and oil as processed into equipment. It also assists the operator in maintaining the oil in serviceable condition.

2. References

This standard shall be used in conjunction with the following publications. When the following standards are superseded by an approved revision, the revision shall apply.

ASTM D88-94 (1999), Standard Test Method for Saybolt Viscosity.[2]

ASTM D92-02, Standard Test Method for Flash and Fire Points by Cleveland Open Cup.

ASTM D97-02, Standard Test Method for Pour Point of Petroleum Products.

ASTM D445-01, Standard Test Method for Kinematic Viscosity of Transparent and Opaque Liquids (the calculation of Dynamic Viscosity).

ASTM D6l1-01b, Standard Test Methods for Aniline Point and Mixed Aniline Point of Petroleum Products and Hydrocarbon Solvents.

ASTM D664-01, Standard Test Method for Acid Number of Petroleum Products by Potentiometric Titration.

ASTM D877-00, Standard Test Method for Dielectric Breakdown Voltage of Insulating Liquids Using Disk Electrodes.

ASTM D923-97, Standard Practices for Sampling Electrical Insulating Liquids.

ASTM D924-99e1, Standard Test Method for Dissipation Factor (or Power Factor) and Relative Permittivity (Dielectric Constant) of Electrical Insulating Liquids.

ASTM D971-99a, Standard Test Method for Interfacial Tension of Oil Against Water by the Ring Method.

ASTM D974-02, Standard Test Method for Acid and Base Number by Color-Indicator Titration.

ASTM D1275-96a, Standard Test Method for Corrosive Sulfur in Electrical Insulating Oils.

ASTM D1298-99, Standard Practice for Density, Relative Density (Specific Gravity), or API Gravity of Crude Petroleum and Liquid Petroleum Products by Hydrometer Method.

ASTM Dl500-98, Standard Test Method for ASTM Color of Petroleum Products (ASTM Color Scale).

[2]ASTM publications are available from the American Society for Testing and Materials, 100 Barr Harbor Drive, West Conshohocken, PA 19428-2959, USA (http://www.astm.org/).

Copyright © 2002 IEEE. All rights reserved.

Copyright The Institute of Electrical and Electronics Engineers, Inc.
Provided by IHS under license with IEEE
No reproduction or networking permitted without license from IHS Not for Resale

ASTM D1524-94 (1999), Standard Test Method for Visual Examination of Used Electrical Insulating Oils of Petroleum Origin in the Field.

ASTM D1533-00, Standard Test Methods for Water in Insulating Liquids by Coulometric Karl Fischer Titration.

ASTM Dl816-97, Standard Test Method for Dielectric Breakdown Voltage of Insulating Oils of Petroleum Origin Using VDE Electrodes.

ASTM D2112-01a, Standard Test Method for Oxidation Stability of Inhibited Mineral Insulating Oil by Pressure Vessel.

ASTM D2l6l-93 (1999) e2, Standard Practice for Conversion of Kinematic Viscosity to Saybolt Universal Viscosity or to Saybolt Furol Viscosity.

ASTM D2285-99, Standard Test Method for lnterfacial Tension of Electrical Insulating Oils of Petroleum Origin Against Water by the Drop-Weight Method.

ASTM D2300-00, Standard Test Method for Gassing of Insulating Liquids Under Electrical Stress and Ionization (Modified Pirelli Method).

ASTM D2440-99, Standard Test Method for Oxidation Stability of Mineral Insulating Oil.

ASTM D2668-96, Standard Test Method for 2, 6-Ditertiary-Butyl Para Cresol and 2, 6-Ditertiary-Butyl Phenol in Electrical Insulating Oil by Infrared Absorption.

ASTM D2945-90 (1998), Standard Test Method for Gas Content of Insulating Oils.

ASTM D3284-99, Standard Test Method for Combustible Gases in the Gas Space of Electrical Apparatus Using Portable Meters.

ASTM D3300-00, Standard Test Method for Dielectric Breakdown Voltage of Insulating Oils of Petroleum Origin Under Impulse Conditions.

ASTM D3487-00, Standard Specification for Mineral Insulating Oil Used in Electrical Apparatus.

ASTM D3612-01, Standard Test Method for Analysis of Gases Dissolved in Electrical Insulating Oil by Gas Chromatography.

ASTM D3613-98, Standard Practice for Sampling Insulating Liquids for Gas Analysis and Determination of Water Content.

ASTM D4059-00, Standard Test Method for Analysis of Polychlorinated Biphenyls in Insulating Liquids by Gas Chromatography.

ASTM D4768-96, Standard Test Method for Analysis of 2, 6-Ditertiary-Butyl Para-Cresol and 2, 6-Dietertiary-Butyl Phenol in Insulating Liquids by Gas Chromatography.

ASTM D5837-99, Standard Test Method for Furanic Compounds in Electrical Insulating Liquids by High-Performance Liquid Chromatography (HPLC).

Copyright © 2002 IEEE. All rights reserved.

Copyright The Institute of Electrical and Electronics Engineers, Inc.
Provided by IHS under license with IEEE
No reproduction or networking permitted without license from IHS Not for Resale

IEEE Std 62-1995, IEEE Guide for Diagnostic Field Testing of Electric Power Apparatus—Part 1: Oil Filled Power Transformers, Regulators, and Reactors.[3, 4]

IEEE Std 637™-1985 (R1992), IEEE Guide for the Reclamation of Insulating Oil and Criteria for its Use.

IEEE Std 980™-1994 (R2001), IEEE Guide for Containment and Control of Oil Spills in Substations.

IEEE Std C37.010™-1999, IEEE Application Guide for AC High-Voltage Circuit Breakers Rated on a Symmetrical Current Basis.

IEEE Std C57.93™-1995 (R2001), IEEE Guide for Installation of Liquid-Immersed Power Transformers.

IEEE Std C57.104-1991, IEEE Guide for the Interpretation of Gases Generated in Oil-Immersed Transformers.

IEEE Std C57.121™-1998, IEEE Guide for Acceptance and Maintenance of Less-Flammable Hydrocarbon Fluid in Transformers.

IEEE Std C57.131™-1995, IEEE Standard Requirements for Load Tap Changers.

Title 40 Code of Federal Regulations Part 110, Discharge of Oil.[5]

Title 40 Code of Federal Regulations Part 112.7, Guidelines for the Preparation and Implementation of a Spill Prevention Control and Counter Measure Plan.

Title 40 Code of Federal Regulations Part 761, Polychlorinated Biphenyls (PCBs) Manufacturing, Processing, Distribution in Commerce, and Use Prohibitions.

3. Definitions

The various tests conducted on the insulating oil are defined and described in Clause 5.

3.1 reclamation of oil: The restoration of usefulness by the removal of contaminants and products of degradation such as polar, acidic, or colloidal materials from used electrical insulating liquids by chemical or adsorbent means such as Fuller's earth.

3.2 reconditioning of oil: The removal of insoluble contaminants, moisture, and dissolved gases from used, electrical insulating liquids by mechanical means, such as vacuum processing or filtering.

4. Evaluation of mineral insulating oil

4.1 General

This guide uses several different terms to identify insulating oil of a petroleum origin, for example, as defined in ASTM D3487-00. The terms *mineral insulating oil*, *liquid*, and *dielectric fluid* are all equivalent to *insulating oil* in the context of this guide.

[3]IEEE publications are available from the Institute of Electrical and Electronics Engineers, 445 Hoes Lane, P.O. Box 1331, Piscataway, NJ 08855-1331, USA (http://standards.ieee.org/).

[4]The IEEE standards referred to in Clause 2 are trademarks belonging to the Institute of Electrical and Electronics Engineers, Inc.

[5]Available from the U.S. Government Printing Office, Superintendent of Documents, Mail Stop SSOP, Washington, DC 20402.

Copyright © 2002 IEEE. All rights reserved.

Copyright The Institute of Electrical and Electronics Engineers, Inc.
Provided by IHS under license with IEEE
No reproduction or networking permitted without license from IHS Not for Resale

4.2 New oil properties

New mineral insulating oils as delivered must conform to the property requirements listed in ASTM D3487-00.

Newly supplied oils have many characteristics related to their chemical and molecular structure that are directly measured by test methods such as viscosity, flash and fire points, pour point, aniline point, relative density (specific gravity), oxidation stability, gassing tendency, and dielectric strength.

Many characteristics not necessarily related to the functional performance of mineral insulating oils are evaluated because of their sensitivity to the presence of harmful contaminants. The following characteristics are sensitive to contamination in the oil: interfacial tension, dissipation factor (power factor), dielectric breakdown voltage, color, water content, and neutralization number (acidity).

4.2.1 New oil properties—as supplied

New mineral insulating oils as supplied must have properties so that new oils meet the standard specification of ASTM D3487-00 and Clause 5 of this guide when received, prior to any processing.

4.2.2 Test limits: new oil properties—as received from the supplier

When mineral insulating oil specified to conform to ASTM D3487-00 is received, it should be tested to verify conformance with ASTM D3487-00. Testing of the oil for full conformance of all property requirements of ASTM D3487-00 is only justified under circumstances determined by the purchaser. As a minimum, it is recommended that the purchaser require the supplier to provide a certified set of tests for the oil that demonstrate that the oil, as shipped, met or exceeded the property requirements of ASTM D3487-00. For those circumstances where a full set of tests according to ASTM D3487-00 are not justified, it is recommended that, at a minimum, the tests shown in Table 1 of this guide be considered. The purchaser of the oil should conduct tests sufficient to satisfy concerns regarding conditions of shipment that might result in nonconformance to ASTM D3487-00 property requirements. Table 1 lists several of the more important tests with values that should help in the decision regarding acceptance of the new mineral insulating oil.

Insulating oil is ordinarily shipped in three types of containers: drums or totes, tank trailers, and rail cars. Rail cars are usually under the control of the supplier and dedicated to insulating oil shipment, so they tend to be the cleanest. Highway trailers are used to transport many different chemical products as well as insulating oil; these trailers are therefore subject to chemical contamination. Special cleaning and drying procedures may be necessary. If problems are encountered, check the history of the shipping containers to see that they have been cared for properly. It is recommended that the purchaser require the delivery of oil in containers that are properly cleaned to guarantee delivery of oil conforming to ASTM D3487-00.

Drums and totes are the least desirable method of insulating oil transport but may be necessary for small purchases. Drums and totes should be stored under cover to prevent contamination by moisture. Before processing, it is necessary to check the quality of the oil in each drum or tote or after blending the oil in a large tank. Each tank load or each shipping unit of oil as received at the customer's site should undergo a check test to determine that the electrical characteristics have not been impaired during transit or storage. Table 1 contains a list of recommended acceptance tests for shipments of mineral insulating oil as received from the supplier. Some users may not wish to perform all these tests; however, as a minimum, dielectric strength and dissipation factor (power factor) as listed in Table 1 should be performed. It is satisfactory to accept oils that exhibit characteristics other than those described by the values in Table 1, providing that the users and the suppliers are in agreement.

Copyright © 2002 IEEE. All rights reserved.

Copyright The Institute of Electrical and Electronics Engineers, Inc.
Provided by IHS under license with IEEE
No reproduction or networking permitted without license from IHS
Not for Resale

4.3 New oil properties—oil received in new equipment rated less than 230 kV

Mineral insulating oil that has been shipped in new equipment from the manufacturing plant may be evaluated by obtaining a sample from the equipment at the job site. Note that the new oil characteristics will have changed. The oil may have been filtered and dried at the factory. The more sensitive dielectric breakdown test, ASTM Dl816-97, is a recommended test. Properties, such as interfacial tension (IFT), dielectric strength, and dissipation factor, which are sensitive to certain dissolved or particulate contaminants, will reflect the exposure to normal equipment construction materials. Recommended test limits for mineral insulating oil received in new equipment rated less than 230 kV prior to energization are given in Table 2 of this guide. Table 2 allows for change due to oil contacting transformer materials.

Table 1—Test limits for shipments of new mineral insulating oil as received from the supplier

Test and method	Limit value
Dielectric strength[a], ASTM D1816-97, kV minimum,	
1 mm gap[b]:	20
2 mm gap[b]:	35
Dissipation factor (power factor), ASTM D924-99e1	
25 ºC, % maximum:	0.05
100 °C, % maximum:	0.30
Interfacial tension, ASTM D971-99a,	
mN/m minimum:	40
Color, ASTM D1500-98,	
ASTM units maximum:	0.5
Visual examination, ASTM D1524-94 (1999):	Bright and clear
Neutralization number (acidity), ASTM D974-02	
mg KOH/g maximum:	0.015[c]
Water content, ASTM D1533-00	
mg/kg maximum[d]:	25[c]
Oxidation inhibitor content when specified, ASTM D2668-96	
Type I oil, % maximum:	0.08
Type I oil, % minimum:	0.0
Type II oil, % maximum:	0.3
Type II oil, % minimum:	>0.08
Corrosive sulfur, ASTM D1275-96a	Not corrosive
Relative density (specific gravity), ASTM D1298-99	
15 °C/15 °C maximum:	0.91

[a]Oil dielectric testing in accordance with ASTM D877-00 has been replaced by ASTM D1816-97 in Table 1. See 5.2.1.
[b]Alternate measurements of 0.04 in and 0.08 in respectively for gaps.
[c]This value is more stringent than the ASTM D3487-00 requirement.
[d]Equivalent measurement is parts per million, ppm.

--`,,`,,`,,`,,`,,`,,`---
Copyright © 2002 IEEE. All rights reserved.

Copyright The Institute of Electrical and Electronics Engineers, Inc.
Provided by IHS under license with IEEE
No reproduction or networking permitted without license from IHS
Not for Resale

Table 2—Test limits for new mineral insulating oil received in new equipment, below 230 kV, prior to energization

Test and method	Value for voltage class	
	≤ 69kV	> 69 – <230 kV
Dielectric strength[a], ASTM D1816-97, kV minimum,		
1 mm gap[b]:	25	30
2 mm gap[b]:	45	52
Dissipation factor (power factor), ASTM D924-99e1,		
25 ºC, % maximum:	0.05	0.05
100 °C, % maximum:	0.40	0.40
Interfacial tension, ASTM D971-99a,		
mN/m minimum:	38	38
Color, ASTM D1500-98,		
ASTM units maximum:	1.0	1.0
Visual examination, ASTM D1524-94 (1999):	Bright and clear	Bright and clear
Neutralization number (acidity), ASTM D974-02,		
mg KOH/g maximum:	0.015[c]	0.015[c]
Water Content, ASTM D1533-00,		
mg/kg maximum[d]:	20	10
Oxidation inhibitor content when specified, ASTM D2668-96,		
Type I oil, % maximum:	-	0.08
Type I oil, % minimum:	-	0.0
Type II oil, % maximum:	0.3	0.3
Type II oil, % minimum:	>0.08	>0.08

[a]Oil dielectric testing in accordance with ASTM D877-00 has been replaced by ASTM D1816-97 in Table 2. See 5.2.1.
[b]Alternate measurements of 0.04 in and 0.08 in respectively for gaps.
[c]This value is more stringent than the ASTM D3487-00 requirement.
[d]Equivalent measurement is parts per million, ppm.

4.4 New oil properties—after filling into new equipment rated at 230 kV or higher

Prior to filling equipment rated 230 kV and above with mineral insulating oil at the installation site, manufacturers generally require rigorous processing of the oil to remove all moisture, particulate matter, and gas that dissolved during shipment. The object is to fill high-voltage equipment with oil that contains the very least amount of particulate (see also IEEE Std 62-1995) material and water, recognizing that a slight reduction in quality due to contact with the equipment insulation and other materials will occur. In this procedure, oil samples are taken after the oil enters into the electrical equipment.

Copyright © 2002 IEEE. All rights reserved.

Copyright The Institute of Electrical and Electronics Engineers, Inc.
Provided by IHS under license with IEEE
No reproduction or networking permitted without license from IHS
Not for Resale

When mineral insulating oil is received in bulk shipping containers, it is processed according to the instructions of the manufacturer and then introduced into the equipment. Table 3 contains test limits that ensure that the insulating oil, in equipment after the processing and standing time before energization, is dry, contains no excess particulate matter, and contains a minimum amount of dissolved gas.

Table 3—Test limits for new mineral insulating oil processed for equipment, 230 kV class and above, prior to energization

Test and method	Value for voltage class	
	≥ 230 kV – < 345 kV	345 kV and above
Dielectric strength. ASTM D1816-97, kV minimum, 1 mm gap[a]: 2 mm gap[a]:	 32 55	 35 60
Dissipation factor (power factor), ASTM D924-99e1, 25 ºC, % maximum: 100 °C, % maximum:	 0.05 0.30	 0.05 0.30
Interfacial tension, ASTM D971-99a, mN/m minimum:	 38	 38
Color, ASTM D1500-98, ASTM units maximum:	 1.0	 0.5
Visual examination, ASTM D1524-94 (1999):	Bright and clear	Bright and clear
Neutralization number (acidity), ASTM D974-02, mg KOH/g maximum:	 0.015[b]	 0.015[b]
Water content, ASTM D1533-00, mg/kg maximum[d]:	 10	 10
Total dissolved gas, ASTM D2945-90 (1998):	0.5% or per manufacturer's requirements[c].	0.5% or per manufacturer's requirements[c].

[a]Alternate measurements of 0.04 in and 0.08 in respectively for gaps.
[b]This value is more stringent than the ASTM D3487-00 requirement.
[c]This value should be obtained from a sample collected 24 to 48 h after the transformer is filled, and applies only to transformers with diaphragm conservator systems.
[d]Equivalent measurement is parts per million, ppm.

4.5 Percent saturation of water in mineral oil (see also 6.3.12 of IEEE Std 62-1995)

The quantity of dissolved and dispersed water in insulating fluids is significant for two reasons: 1) The presence of polar water molecules in the fluid adversely affects the dielectric properties of the fluid, and 2) The amount of moisture in the oil can be reflective of the amount of moisture in the paper insulation. The solubility of water in a dielectric fluid is temperature dependent, so a statement regarding mg/kg of water in

--`,,`-`-`,,`,,`,`,,`---
Copyright © 2002 IEEE. All rights reserved.
Copyright The Institute of Electrical and Electronics Engineers, Inc.
Provided by IHS under license with IEEE
No reproduction or networking permitted without license from IHS
Not for Resale

the oil without temperature information would not be adequate. The calculation of the percent water saturation, (mg/kg water/mg/kg of water at saturation) × 100, has a greater significance as it indicates the possibility of free water formation in the oil. Free water in the oil results in unacceptable dielectric strength values. Water partitions between paper insulation and oil. This partition coefficient is temperature dependent so the water will move between the paper insulation and the oil as the temperature changes. For example, if the temperature increases, movement of water is from the paper to the oil. This increase in water content of the oil will increase the percent saturation and could result in free water formation, should the temperature of the oil decrease rapidly. Table 4 provides general guidelines for the interpretation of data expressed in percent saturation.

The following is an example of determining the percent saturation of water in mineral oil (see Bruce, C. M., Christie, J. D., and Griffen. Paul [B1]):

$$\log_{10} S_0 = (-1567/T) + 7.0895 \quad (1)$$

where

S_0 is the solubility of water in mineral oil
T is the absolute temperature in kelvins

$$\% \text{ saturation} = 100(\text{mg/kg of water})/S_0 \quad (2)$$

Example:

If

Water content = 11 mg/kg
Temperature of top oil = 30 °C

then

$$\log_{10} S_0 = (-1567/303) + 7.0895 = -5.1716 + 7.0895 = 1.9179$$

$$S_0 = 82.775$$

$$\% \text{ saturation} = 100(11/82.775) = 13$$

Table 4—General guidelines for interpreting data expressed in percent saturation[a]

Percent saturation water-in-oil	Condition of cellulosic insulation
0–5	Dry insulation
6–20	Moderate—wet, low numbers indicate fairly dry to moderate levels of water in the insulation. Values toward the upper limit indicate moderately wet insulation.
21–30	Wet insulation
>30	Extremely wet insulation

[a]Table 4 of this standard is Table 7 of IEEE Std 62-1995.

Copyright © 2002 IEEE. All rights reserved.

Copyright The Institute of Electrical and Electronics Engineers, Inc.
Provided by IHS under license with IEEE
No reproduction or networking permitted without license from IHS
Not for Resale

Table 5 illustrates conditions of moisture content in an operating unit.

Table 5—Recommended maximum limit of water content in mineral insulating oil of operating gas blanketed, sealed, or diaphragm conservator transformers[a]

Average oil temperature	Suggested maximum water contents in mg/kg and percent saturation[b]					
	50 ºC		60 ºC		70 ºC	
	mg/kg[c]	% saturation	mg/kg[c]	% saturation	mg/kg[c]	% saturation
≤ 69kV	27	15	35	15	55	15
>69 – <230 kV	12	8	20	8	30	8
230 kV and greater	10	5	12	5	15	5

NOTES

1—These values are by necessity approximate, but are adequate for maximum water in oil guides.

2—The oil sample should, if practical, be taken when the load and oil temperatures have been relatively constant for 48 hours. The intent is to obtain a sample when the moisture content in the transformer is close to equilibrium. If the load and/or ambient are variable, the oil temperature can be maintained relatively constant by controlling the amount of cooling in operation. If you are confident that the temperature gauges are in calibration then record the top oil temperature at the time that the sample is taken. For Oil Natural Air Natural (ONAN) and Oil Natural Air Forced (ONAF) ratings, subtract 10 °C from the top oil to obtain the average oil temperature. If you are unsure of the gauge accuracy, record the actual sample temperature and add 5 °C to approximate the average oil temperature.

3—The above values are based on the following approximate percent by weight of water in insulation values (see IEEE Std 62-1995):

≤ 69kV	3% maximum
>69 - < 230 kV	2% maximum
230 kV and greater	1.25% maximum

4—Saturation values (mg/kg) at 100% saturation:

50 ºC	175
60 ºC	245
70 ºC	335

[a]The data in Table 5 is from sealed transformers and may also apply to free breathing type transformers.
[b]Calculated from formulas 1 and 2 in Clause 4.4 from Bruce, C. M., Christie, J. D., and Griffen. Paul [B1].
[c]Equivalent measurement is parts per million, ppm.

4.6 Mixtures of mineral insulating oil

Although conventional mineral oils from different suppliers may differ in their characteristics, these oils, as well as blends of these oils, should all meet the specifications of ASTM D3487-00.

Although mineral insulating oil is miscible with some types of less flammable and nonflammable dielectric liquids, it is advisable to use dedicated processing and handling systems for each different type of fluid in order to avoid even traces of cross-contamination, particularly even trace contamination between petroleum based and non-petroleum based fluids.

Mixtures of less flammable or nonflammable dielectric fluids with conventional mineral insulating oil will alter the flammability characteristics of the less flammable fluid. Differences in the dielectric constant of the fluids may cause localized voltage stresses in equipment. It is undesirable to mix different types of dielectric fluids.

Copyright © 2002 IEEE. All rights reserved.

Copyright The Institute of Electrical and Electronics Engineers, Inc.
Provided by IHS under license with IEEE
No reproduction or networking permitted without license from IHS
Not for Resale

4.7 Sampling

Accurate sampling methods are extremely important due to their effect on the reliability of the test results for the sampled oil. Careless sampling procedures will result in contamination of the sample. This will lead to erroneous conclusions concerning the quality of the oil. In order to minimize the possibility of obtaining a non-representative sample, the procedures and precautions outlined in the latest revision of ASTM D923-97, and/or ASTM D3613-98 should be followed.

WARNING

Caution should be taken when extracting an oil sample from energized equipment. Taking samples from equipment under negative pressure (vacuum) may cause an air bubble to be drawn into the tank. If this occurs, it can cause catastrophic failure and death.

5. Oil tests and their significance

There are many established ASTM tests of practical significance that can be applied to insulating oil. Some of these tests are more applicable to new oils than to service-aged oils; some are more useful in the analysis of service-aged oils than oils received in new condition, particularly trace contamination between petroleum based and non-petroleum based fluids.

Each of the tests and their significance are described in the subclauses of this guide, listed in Table 6. The number following the name of the test is the number of the ASTM standard/method.

Table 6—Pertinent ASTM tests for mineral insulating oil

Subclause	Test	ASTM standard/method
5.1 Physical tests		
5.1.1	Aniline point	ASTM D611-01b
5.1.2	Color	ASTM D1500-98
5.1.3	Flash and fire points	ASTM D92-02
5.1.4	Interfacial tension	ASTM D971-99a ASTM D2285-99
5.1.5	Pour point	ASTM D97-02
5.1.6	Relative density (specific gravity)	ASTM D1298-99
5.1.7	Viscosity	ASTM D88-94 (1999) ASTM D445-01 ASTM D2161-93 (1999)
5.1.8	Visual examination	ASTM D1524-94 (1999)

Copyright © 2002 IEEE. All rights reserved.

Copyright The Institute of Electrical and Electronics Engineers, Inc.
Provided by IHS under license with IEEE
No reproduction or networking permitted without license from IHS
Not for Resale

Table 6—Pertinent ASTM tests for mineral insulating oil (continued)

Subclause	Test	ASTM standard/method
5.2 Electrical tests		
5.2.1	Dielectric breakdown voltage	ASTM D877-00 ASTM D1816-97
5.2.2	Dielectric breakdown impulse voltage	ASTM D3300-00
5.2.3	Dissipation factor (power factor)	ASTM D924-99e1
5.2.4	Gassing of insulating oils under electrical stress and ionization	ASTM D2300-00
5.3 Chemical tests		
5.3.1	Gas content	ASTM D2945-90 (1998) ASTM D3284-99 ASTM D3612-01
5.3.2	Polychlorinated biphenyls	ASTM D4059-00
5.3.3	Corrosive sulfur	ASTM D1275-96a
5.3.4	Neutralization number (acidity)	ASTM D664-01 ASTM D974-02
5.3.5	Oxidation inhibitor content	ASTM D2668-96 ASTM D4768-96
5.3.6	Oxidation stability (inhibited oil only, BOMB) Oxidation stability	ASTM D2112-01a ASTM D2440-99
5.3.7	Water in insulating liquids	ASTM D1533-00
5.3.8	Furans in insulating liquids	ASTM D5837-99

5.1 Physical tests

5.1.1 Aniline point—ASTM D611-01b

The aniline point (temperature) of a mineral insulating oil indicates the solvency of the oil for some materials that are in contact with the oil. A high aniline point indicates a lower degree of aromaticity and a lower solvency for some material (rubber, for example).

5.1.2 Color—ASTM D1500-98

Insulating oil should have a light color and be optically clear so that it permits visual inspection of the assembled apparatus inside the equipment tank. Any change in the color of an oil over time is an indication of deterioration or contamination of the oil.

Copyright © 2002 IEEE. All rights reserved.

Copyright The Institute of Electrical and Electronics Engineers, Inc.
Provided by IHS under license with IEEE
No reproduction or networking permitted without license from IHS Not for Resale

5.1.3 Flash and fire points—ASTM D92-02

The flash point of an oil is the temperature to which the material must be heated (under prescribed conditions of test) in order to give off sufficient vapor to form a flammable mixture with air. The fire point is the temperature that provides sufficient oil vapors to ignite and sustain a fire for 5 seconds (under the same test conditions). A low flash point indicates the presence of volatile combustible contaminants in the insulating oil.

5.1.4 Interfacial tension—ASTM D971-99a, ASTM D2285-99

This method covers the measurement, under nonequilibrium conditions, of the surface tension that an insulating fluid maintains against water. Interfacial tension is a measurement of the forces of attraction between molecules of the two fluids. It is expressed in millinewtons per meter (mN/m). The test is an excellent means of detecting oil-soluble polar contaminants and oxidation products in insulating oils.

5.1.5 Pour point—ASTM D97-02

The pour point is the temperature at which oil ceases to flow under prescribed testing conditions. The pour point has little significance as a test for contamination or deterioration of the oil. It may be useful for oil identification and determination of suitability for a particular climate.

5.1.6 Relative density (specific gravity)—ASTM D1298-99

The relative density of oil is the ratio of the weights of equal volumes of the oil and water, tested at 15 °C. The relative density is significant in determining the suitability for use in certain applications; in cold climates, ice may form in equipment exposed to temperatures below freezing. When considered along with other oil properties, relative density can be an indicator of the quality of the oil.

5.1.7 Viscosity—ASTM D88-94 (1999), ASTM D445-01, ASTM D2161-93 (1999)

The viscosity of insulating oil is measured by timing the flow of a known volume of oil through a calibrated tube. Viscosity is not significantly affected by oil contamination or deterioration, but may be useful for identifying certain types of service-aged insulating oils. Viscosity has an important influence on the heat transfer characteristics of oil. High viscosity decreases the cooling efficiency of the oil. High viscosity will also affect the movement of parts in electrical equipment, such as circuit breakers, switchgear, tap changers, pumps, and regulators. Viscosity is a factor in determining the conditions for oil processing and cellulose impregnation time.

5.1.8 Visual examination—ASTM D1524-94 (1999)

This test indicates the color and degree of turbidity of oil, which may indicate the presence of free water or contaminating solid particles. The source of insoluble solid contaminants may be determined by filtrating the particles and examining them. This test may be used to suggest the need for additional laboratory tests, as it may permit a determination of whether the sample should be sent to a central laboratory for a full evaluation.

5.2 Electrical tests

5.2.1 Dielectric breakdown voltage—ASTM D877-00, ASTM D1816-97

The dielectric breakdown voltage of insulating oil is a measure of its ability to withstand voltage stress without failure. It is the voltage at which breakdown occurs between two electrodes under prescribed test conditions. The test serves primarily to indicate the presence of electrically conductive contaminants in the

Copyright © 2002 IEEE. All rights reserved.

Copyright The Institute of Electrical and Electronics Engineers, Inc.
Provided by IHS under license with IEEE
No reproduction or networking permitted without license from IHS
Not for Resale

oil, such as water, dirt, moist cellulosic fibers, or particulate matter. A high dielectric breakdown voltage does not indicate the absence of all contaminants, however.

The electrodes described in ASTM D877-00 are thin flat disks, which are not representative of the electrodes in transformers. Although the rounded electrodes described in ASTM D1816-97 do not duplicate the characteristics of insulated electrodes in transformers, they more closely approximate transformer applications. However, the electrodes described in ASTM D1816-97 are more responsive to particles and dissolved water in oil, both of which are detrimental to the electrical strength of oil in transformers. Therefore, test results in ASTM D1816-97 furnish a better evaluation of changes that may occur in the oil from transformers.

Two methods are recognized for measuring the dielectric breakdown voltage of insulating oils:

a) ASTM D877-00 is recommended for the routine acceptance of new, unprocessed oil from a supplier for use in circuit breakers. This test method uses thin flat-faced cylindrical electrodes with a 2.5 mm gap. The sensitivity of this method, to the general population of contaminates present in a liquid sample, decreases as applied test voltages used in this method become greater than 25 kV rms.
b) ASTM D18l6-97 is recommended for testing fluid that is being processed into transformers or contained in transformers and load tap changers. This method uses spherically shaped electrodes. The fluid sample is circulated continuously in the test cell throughout the test. The gap distance standard settings are 1 mm and 2 mm.

5.2.2 Dielectric breakdown impulse voltage—ASTM D3300-00

This test method is most commonly performed using a negative polarity point opposing a grounded sphere (NPS). The NPS breakdown voltage of fresh unused oils measured in the highly divergent field in this configuration depends on oil composition; decreasing with increasing concentration of aromatic, particularly polyaromatic, hydrocarbon molecules.

This test method may be used to evaluate the continuity of composition of oil from shipment to shipment. The NPS impulse breakdown voltage of oil can also be substantially lowered by contact with materials of construction, by service aging, and by other impurities. Test results lower than those expected for a given fresh oil may also indicate use or contamination of that oil.

Although polarity of the voltage wave has little or no effect on the breakdown strength of oil in uniform fields, polarity does have a marked effect on the breakdown voltage of oil in nonuniform electric fields.

Transient voltages may also vary over a wide range in both the time to reach crest value and the time to decay to half crest or to zero magnitude. The standard lightning impulse test described in IEEE Std C57.12.90-1999 [B2] specifies a 1.2 × 50-ms negative polarity wave.

5.2.3 Dissipation factor (power factor)—ASTM D924-99e1

The dissipation factor is a measure of the power lost when an electrical insulating liquid is subjected to an ac field. The power is dissipated as heat within the fluid. A low-value dissipation factor means that the fluid will cause little of the applied power to be lost. The test is used as a check on the deterioration and contamination of insulating oil because of its sensitivity to ionic contaminants.

5.2.4 Gassing of insulating oils under electrical stress and ionization—ASTM D2300-00

This test measures whether insulating oils are gas absorbing or gas evolving when subjected to electrical voltage. For certain applications, when insulating oils are stressed at high voltage gradients, it is desirable to know the rate at which gas is absorbed or evolved from the oil. The absorption or evolution of gas by a liquid under electrical stress is a function of the aromatic character of the liquid molecules. Liquids that are significantly aromatic in character will absorb gas as they are electrically stressed. Liquids that have little or no

Copyright © 2002 IEEE. All rights reserved.

Copyright The Institute of Electrical and Electronics Engineers, Inc.
Provided by IHS under license with IEEE
No reproduction or networking permitted without license from IHS Not for Resale

aromatic character will evolve hydrogen gas upon application of an electrical voltage. At the present time, however, correlation of these test results with equipment performance is limited. Numerical results obtained in different laboratories or by using two different procedures may differ significantly in magnitude, and the results of this method should be considered qualitative in nature.

5.3 Chemical tests

5.3.1 Gas content—ASTM D2945-90 (1998), ASTM D3284-99, ASTM D3612-01

The gas content of an insulating fluid may be defined as the volume of dissolved gas per 100 volumes of oil, at standard pressure and temperature. Some types of equipment require the use of electrical insulating liquids of low gas content. In filling electrical apparatus, a low gas content reduces foaming and also reduces the available oxygen, thereby increasing the service life of the insulating oil.

The amount and kind of gases dissolved in oil can be used as a tool to aid in detecting and diagnosing faults and abnormal operating conditions in equipment.

The test is not intended for use in purchase specifications because the oil is customarily degassed immediately prior to use. The test can be used, however, as a factory control test and is more useful in evaluating the health of the transformer equipment. Overheating or arcing within the transformer will generate combustible and noncombustible gasses that will be dissolved in the oil. For dissolved gas analysis, reference IEEE Std C57.104-1991 for further recommendations.

5.3.2 Polychlorinated biphenyls (PCBs)—ASTM D4059-00

United States regulations require that electrical apparatus and electrical insulating fluids containing polychlorinated biphenyls (PCBs) be handled and disposed of through the use of specific procedures. The procedure to be used for a particular apparatus or quantity of insulating fluid is determined by the PCB content of the fluid. The results of this analytical technique can be useful in selecting the appropriate handling and disposal procedures; refer to Title 40 Code of Federal Regulations Part 761.

5.3.3 Corrosive sulfur—ASTM D1275-96a

This test is designed to detect the presence of free sulfur and combined corrosive sulfur by how the liquid affects polished copper strips in prescribed conditions. The test indicates the possibility of corrosion inside of electrical equipment resulting from the presence of sulfur-containing compounds. The source of sulfur present in insulating oil is usually the crude oil from which it is refined. The sulfur may come from rubber hoses used for oil processing or from replacement gasket materials.

5.3.4 Neutralization number (acidity)—ASTM D664-01, ASTM D974-02

The neutralization number of an electrical insulating liquid is a measure of the acidic components of that material. In new oil, any acid present is likely residual from the refining process. In a service-aged liquid, the neutralization number is a measure of the acidic byproducts of the oxidation of an oil. The neutralization number may be used as a general guide for determining when oil should be reprocessed or replaced. ASTM D974-02 is the traditional color-change indicator method of titrating the acids with a mild (0.1 N) KOH solution. ASTM D664-01 is a potentiometric titration method. On some service-aged liquids, the color may be so dark as to impair the ability of the technician to determine the indicator color change in ASTM D974-02, so ASTM D664-01 is used instead. The correlation between these two methods, however, has not been established.

Copyright © 2002 IEEE. All rights reserved.

Copyright The Institute of Electrical and Electronics Engineers, Inc.
Provided by IHS under license with IEEE
No reproduction or networking permitted without license from IHS Not for Resale

5.3.5 Oxidation inhibitor content—ASTM D2668-96 by infrared spectrophotometry, ASTM D4768-96 by gas chromatography

There are two synthetic oxidation inhibitors commonly used in dielectric fluids. They are 2-6 ditertiary-butyl phenol (DBP) and 2-6 ditertiary-butyl para-cresol (DBPC). Their use provides added resistance to oxidation in systems that are partially or wholly exposed to air. The effectiveness of the oxidation inhibitor depends a great deal on the type of crude oil from which the insulating oil came. Certain new oils may contain naturally occurring antioxidant substances that may yield a false-positive indication in this test.

5.3.6 Oxidation stability, inhibited only, (BOMB)—ASTM D2112-01a, ASTM D2440-99

Oxidation stability—ASTM D2112-01a: This test method is a rapid test for evaluating the oxidation stability of a new mineral insulating oil that contains the synthetic oxidation inhibitor 2-6 DBPC or 2-6 DBP. The test measures the length of time required for the oil sample to react with a given volume of oxygen when a sample of oil is heated and oxidized under test conditions.

Oxidation stability—ASTM D2440-99: This test method determines the resistance of mineral insulating oils to oxidation under prescribed accelerated aging conditions. Oxidation stability is measured by the propensity of oils to form sludge and acid products during oxidation. This test method is applicable to new oils, both inhibited and uninhibited.

5.3.7 Water in insulating liquids: Karl Fischer Method—ASTM D1533-00

Water may be present in insulating liquids in several forms. The presence of free water may be indicated by visual examination. The oil will appear cloudy or separated water drops will be seen, probably on the bottom surface. The presence of free water can be remedied by filtration or other means. Dissolved water cannot be detected visually and is normally quantified by physical or chemical means. Dissolved water may affect the dielectric breakdown of insulating oil, however, its significance is determined by several factors including the percent of moisture saturation, and the amount and type of contaminates. The method cited is suitable for the determination of water in insulating oil, and, depending upon conditions of sample handling and methods of analysis, can be used to estimate total water as well as dissolved water in insulating oil. The units of measure of water are mg/Kg. New insulating oil received from the manufacturer normally contains less than 25 mg/kg moisture. New insulating oil should be tested for moisture content. If necessary, applicable measures should be taken to avoid introducing high moisture-content oil into electrical equipment.

5.3.8 Furans in insulating liquids—ASTM D5837-99

Furanic compounds are generated by the degradation of cellulosic materials used in the solid insulation systems of electrical equipment. Furanic compounds which are oil soluble to an appreciable degree will migrate into the insulating liquid. The presence of high concentrations of furanic compounds is significant in that this may be an indication of cellulose degradation from aging or incipient fault conditions. Testing for furanic compounds by high-performance liquid chromatography (HPLC) may be used to complement dissolved gas in oil analysis as performed in accordance with the test method in ASTM D3612-01.

6. Handling and storage

It is not intended that the recommendations given in this guide supersede U. S. federal or local regulations concerning storage, handling, or spill cleanup of insulating liquids.

Copyright © 2002 IEEE. All rights reserved.

Copyright The Institute of Electrical and Electronics Engineers, Inc.
Provided by IHS under license with IEEE
No reproduction or networking permitted without license from IHS
Not for Resale

6.1 Tanks

Direct transfer of the oil from on-site delivery containers into equipment, while recommended, is not always practical if the oil being delivered is to be tested before transfer into the equipment. It may be necessary, therefore, to store the oil in storage tanks temporarily. In these instances, all tanks should conform to applicable federal and local standards and codes. Tanks should be equipped with at least one manhole. The interior of the tanks should be sandblasted, primed, and coated with a coating that is compatible with insulating fluids. Storage tanks should be equipped with drains situated to allow complete emptying of the tank, and with either a desiccant breather or a dry gas blanket. Such tanks are often coated internally to prevent rust. Before use, storage tanks should be thoroughly cleaned, wiped dry with clean rags, and flushed with clean insulating oil.

Collapsible or rubber fabric tanks may be used for short-time storage. Care should be taken to ensure that they are cleaned and thoroughly drained before filling with insulating oil. It is recommended that insulating oil not be held for more than three months in temporary storage tanks. Where that is unavoidable, tanks should be equipped with a dry inert (nitrogen) gas system with which to blanket the oil.

6.2 Oil quality protection in storage

All storage tanks should be equipped with a dry nitrogen gas supply or a desiccant vent dryer to minimize the introduction of moisture into the tank. Proper maintenance of the desiccant is essential.

The desiccant should be protected from outside contaminants and entry into the transformer. Filtration of the incoming air will prevent introduction of airborne particulate materials into the fluid during storage.

6.3 Dikes and curbs

Tanks for storage of insulating oil may be surrounded by dikes or curbs sufficient to contain the entire volume of oil in the tank should a spill occur. Refer to Title 40 Code of Federal Regulations Part 112.7 for spill prevention control and countermeasures (SPCC).

6.4 Processing oil for installation in apparatus

See IEEE Std C57.93-1995. Processing systems consist of oil dehydration, degassifying, and filtration. The user should be advised that static charges can develop when insulating oil flows in pipes, hoses, and tanks. Oil leaving a filter press may be charged to a high potential. To accelerate dissipation of the charge in the oil, ground and bond together the filter press, the piping, the equipment tank, and all bushings or the winding leads during oil flow into any tank. Conduction through oil is slow; therefore, it is desirable to maintain these grounds for at least an hour after the oil flow has been stopped. Remove any explosive gas mixture from any container into which oil is flowing. Arcs can occur from the free surface of the oil even though the previous grounding precautions have been taken.

Equipment used for handling mineral insulating oils should be dedicated for that use, as these oils are very sensitive to contamination. Although mineral insulating oils may be miscible with other types of dielectric fluids, it is advisable to use dedicated processing and handling systems for each different type of fluid. See 4.5 of this standard.

Before filling the electrical apparatus, a vacuum may be drawn on its tank. All insulating oil transfer lines should be flushed through with clean, processed oil. During the filling operations, flow rates should be controlled to the value specified by the manufacturer. The vacuum held on the tank should not exceed the design strength specified by the manufacturer.

Copyright © 2002 IEEE. All rights reserved.

Copyright The Institute of Electrical and Electronics Engineers, Inc.
Provided by IHS under license with IEEE
No reproduction or networking permitted without license from IHS Not for Resale

The filling process may be varied to suit the capabilities of the equipment used and the recommendations of the manufacturer. Filling procedures used should comply with those that are recommended by the fluid and the equipment manufacturers in order to maintain eligibility of the equipment warranty.

7. Classification of service-aged insulating oil

7.1 General

This subject is treated in greater detail in IEEE Std 637-1985. It is not practical to indicate the value of specific tests and recommended test limits for all of the possible existing applications of insulating oil in service. It should be recognized that, with the present state of knowledge, no single test can be used as the sole criterion to estimate the condition of service-aged oil. It is, possible, however, to summarize the value and importance of the current tests and to suggest methods of treatment for the oil being examined. Oils in service may be placed in the classifications described in 7.2.1 through 7.2.3, based upon the composite evaluation of significant characteristics.

7.2 Classification

7.2.1 Class I

This group contains oils that are in satisfactory condition for continued use.

Suggested test limits by voltage class for Class I oils in electrical equipment to remain in continued service are given in Table 7. It is not intended that an oil be removed from service when a single property limit is exceeded or that the oil be left in service until all property values are outside the stated limits. It is difficult to quantify the risk of failure while in service with particular test values. The limits from Table 7 are intended to provide reference points for further evaluation and testing. Each case should be examined individually, and the advice of the manufacturer may be considered.

7.2.2 Class II

This group contains oils that do not meet the dielectric strength and/or water content requirements of Table 7 and should be reconditioned by filter pressing or vacuum dehydration.

7.2.3 Class III

This group contains oils in poor condition that should be reclaimed using Fuller's Earth or an equivalent method.

Oils that do not meet the interfacial tension (IFT), dissipation factor, and neutralization number limits provided in Table 7 should be reclaimed. Oils should not be allowed to deteriorate such that the IFT is below 18, or to a point where oxidation inhibitor content is depleted. Under such conditions considerably greater effort (i.e., more passes of treatment) is required.

For information and advice concerning the different techniques of reconditioning and reclaiming service-aged mineral insulating oils, refer to IEEE Std 637-1985. Reconditioning or reclamation of mineral oils containing PCBs can be a violation of environmental regulations.

Copyright © 2002 IEEE. All rights reserved.

Copyright The Institute of Electrical and Electronics Engineers, Inc.
Provided by IHS under license with IEEE
No reproduction or networking permitted without license from IHS Not for Resale

Table 7—Suggested limits for continued use of service-aged insulating oil (grouped by voltage class) (See also IEEE Std 62-1995.)

Test and method	Value for voltage class		
	≤69 kV	>69 – <230 kV	230 kV and above
Dielectric strength[a], ASTM D1816-97, kV minimum, 1 mm gap[b]: 2 mm gap[b]:	23 40	28 47	30 50
Dissipation factor (power factor)[a], ASTM D924-99e1, 25 °C, % maximum 100 °C, % maximum	0.5 5.0	0.5 5.0	0.5 5.0
Interfacial tension, ASTM D971-99a, mN/m minimum	25	30	32
Neutralization number (acidity), ASTM D974-02, mg KOH/g maximum	0.20	0.15	0.10
Water content	Refer to Table 5		
Oxidation Inhibitor Content, ASTM D2668-96, Type II oil	0.09% minimum, if in original oil.		

[a]Older transformers with inadequate oil preservation systems or maintenance, may have lower values.
[b]Alternate measurements of 0.04 in and 0.08 in respectively for gaps.

8. Insulating oil for circuit breakers

8.1 General

The requirements of insulating oil used in circuit breakers, as distinguished from insulating oil used in transformers, are uniquely different. Modern oil circuit breakers require low viscosity and low pour-point oil since a large percentage of them are used outdoors and, in many cases, at low temperatures. It should be noted that all circuit breakers are “free breathing” (open to the atmosphere through a breathing device). This does not prevent the admittance of humid air to the device. In the case of older oil circuit breakers where the use of higher viscosity oil is deemed necessary, caution and judgment must be exercised. The resultant effects of oil mixing and the addition of oxidation inhibitors upon thermal characteristics must be considered.

Reconditioning of circuit breaker oil is conducted in the same manner as transformer oil. The presence of dissolved heat and arc byproducts is a significant problem in circuit breakers. In most transformers these products should not be present. Oil circuit breakers are usually designed with higher dielectric margins and thermal capacities compared to a transformer. In oil circuit breakers, byproducts are created when the circuit breaker operates. These byproducts, combining with moisture and oxygen in the breaker oil, will contribute to reduced dielectric strength in the circuit breaker. The accumulation of these substances results in the need for cleaning the breaker and reconditioning of the oil. For guidance in the application of circuit breakers, see IEEE Std C37.010-1999.

Copyright © 2002 IEEE. All rights reserved.

Copyright The Institute of Electrical and Electronics Engineers, Inc.
Provided by IHS under license with IEEE
No reproduction or networking permitted without license from IHS Not for Resale

8.2 Testing

Testing methods for circuit breaker oils are the same as those used for insulating oils. Samples are taken in the same manner as for insulating oil, at specified intervals, varying from a few months to annually. Some of the established ASTM tests applicable to mineral insulating oils are more significant to transformers than to circuit breakers, since a circuit breaker is essentially a free-breathing device that operates at ambient temperature.

8.2.1 New oil properties—as refined

New mineral insulating oils as received from the supplier must conform to certain qualifying functional requirements listed in ASTM D3487-00.

8.2.2 Test limits: shipments of new mineral insulating oil

When mineral insulating oil meeting the property requirements of ASTM D3487-00 is received in the field for installation in circuit breakers, it should be checked for certain key values that may be affected by shipment and storage. These values are shown in Table 8. Some users may wish to perform additional tests outlined in ASTM D3487-00; however, as a minimum, the tests listed in Table 8 should be performed.

Viscosity [12 cSt (12 mm^2/s) maximum at 40 °C—see ASTM D445-01] and pour point (–40 °C, maximum—see ASTM D97-02) should be checked in cold climates to ensure that the oil does not interfere with the free operation of the equipment.

8.2.3 New oil properties—oil shipped in new equipment

Oil circuit breakers are normally shipped from the factory without oil in the tank(s). New oil is processed on-site and the equipment is filled with the oil. In cases such as these, refer to Table 9.

8.2.4 New oil properties—prior to energizing

When mineral insulating oil is received in bulk shipping containers, it is processed according to the instructions of the manufacturer and then introduced into the equipment. Table 9 gives test limits for mineral circuit breaker insulating oil after being processed, placed in equipment, and allowing for standing times before energizing.

8.2.5 Service-aged oil properties

Suggested limits for continued use of service-aged circuit breaker oils are shown in Table 10.

If additional tests are desired, they should be made in accordance with the guidelines given for insulating oil testing earlier in this guide. Some users of circuit breakers recondition or change their oils without testing them after a preset number of operations.

Copyright © 2002 IEEE. All rights reserved.

Copyright The Institute of Electrical and Electronics Engineers, Inc.
Provided by IHS under license with IEEE
No reproduction or networking permitted without license from IHS Not for Resale

Table 8—Test limits for shipments of new mineral insulating oil for circuit breakers

Test and method	Suggested limit
Dielectric strength, ASTM D1816-97[a], kV minimum, 1 mm, gap[b] 2 mm, gap[b]	 20 35
Dissipation factor (power factor), ASTM D924-99e1, 25 °C, % maximum 100 °C, % maximum	 0.05 0.30
Interfacial tension, ASTM D971-99a, mN/m minimum	 40
Color, ASTM D1500-98, ASTM units maximum	 0.5
Visual examination, ASTM D1524-94 (1999)	 Bright and clear
Neutralization number (acidity), ASTM D974-02, mg KOH/g maximum	 0.015
Water content, ASTM Dl533-00, mg/kg maximum[c]	 25[d]

[a]Oil dielectric testing in accordance with ASTM D877-00 has been replaced by ASTM D1816-97 in this table. See 5.2.1.
[b]Alternate measurements of 0.04 in and 0.08 in respectively for gaps.
[c]Equivalent measurement is parts per million, ppm.
[d]The value of water content is more stringent than the requirement specified in ASTM D3487-00.

Copyright © 2002 IEEE. All rights reserved.

Copyright The Institute of Electrical and Electronics Engineers, Inc.
Provided by IHS under license with IEEE
No reproduction or networking permitted without license from IHS
Not for Resale

Table 9—Test limits—new circuit breaker insulating oil after processing and filling, immediately prior to energizing

Test and method	Suggested limit
Dielectric strength, ASTM D1816-97, kV minimum, 1 mm, gap[a] 2 mm, gap[a]	 30 60
Dissipation factor (power factor), ASTM D924-99e1, 25 °C, % maximum	 0.10
Interfacial tension, ASTM D971-99a, mN/m minimum	 35
Color, ASTM D1500-98, ASTM units maximum	 0.5
Visual Examination, ASTM D1524-94 (1999)	 Bright and clear
Neutralization number (acidity), ASTM D974-02, mg KOH/g maximum	 0.015
Water content, ASTM Dl533-00, mg/kg maximum[b]	 20

[a]Alternate measurements of 0.04 in and 0.08 in respectively for gaps.
[b]Equivalent measurement is parts per million, ppm.

Copyright © 2002 IEEE. All rights reserved.
--`,,`-`-`,,`,,`,`,,`---
Copyright The Institute of Electrical and Electronics Engineers, Inc.
Provided by IHS under license with IEEE
No reproduction or networking permitted without license from IHS
Not for Resale

Table 10—Suggested limits for continued use of service-aged circuit breaker insulating oil

Test and method	Suggested limit
Dielectric strength, ASTM D877-00, kV minimum	25
Dielectric strength, ASTM D1816-97, kV minimum, 1 mm, gap[a] 2 mm, gap[a]	 20 27
Dissipation factor (power factor), ASTM D924-99e1, 25 °C, % maximum	1.0
Interfacial tension, ASTM D971-99a, mN/m minimum	25
Color, ASTM D1500-98, ASTM units maximum	2.0
Visual examination, ASTM D1524-94 (1999)	No excessive carbon in oil.

[a]Alternate measurements of 0.04 in and 0.08 in respectively for gaps.

8.3 Reconditioning

The chief problem in circuit breaker oil maintenance is to keep the fluid free of water, arc decomposition products, and other contaminants. If visual examination shows the presence of these materials and the dielectric strength of the oil drops below an acceptable value, the oil can be reconditioned, provided it is free of chemical contaminants. The accepted means of reconditioning is by using blotter papers or paper cartridge filters. This subject is discussed in detail in IEEE Std 637-1985.

9. Insulating oil for load tap changers (LTCs)

9.1 General

The requirements of insulating oils used in load tap changers (LTCs) are comparable to those of insulating oils used in power transformers. For LTCs where oil is used for arc-quenching, the arcing at the arcing switch or arcing tap switch contacts causes contact erosion and carbonization of the arcing switch oil. The degree of contamination depends upon the operating current and step-voltage of the LTC, the number of operations, and, to some degree, on the quality of the insulating oil (not relevant in case of LTCs with vacuum interrupters).

If the LTC is a “free-breathing” design, the desiccant should be checked periodically to prevent the admittance of humid air.

Copyright © 2002 IEEE. All rights reserved.

Copyright The Institute of Electrical and Electronics Engineers, Inc.
Provided by IHS under license with IEEE
No reproduction or networking permitted without license from IHS
Not for Resale

Maintenance and inspection intervals depend on the type of LTC, the LTC rated through-current, the field experience, and the individual operating conditions. They are suggested as periodic measures with respect to a certain number of operations or after a certain operating time, whichever comes first. The recommended maintenance intervals for an individual LTC type are given in the operating and inspection manuals available for each LTC type. In general, at inspections the oil will be reconditioned or changed.

9.2 Testing methods

Testing methods for LTCs oils are the same as those used for insulating oils of power transformers. Samples are taken in the same manner and at the same intervals as for insulating oils used in power transformers.

9.2.1 New oil properties—as supplied

New mineral insulating oils as received from the supplier must conform to certain qualifying functional requirements listed in ASTM D3487-00.

9.2.2 Test limits—shipment of new mineral insulating oil

When mineral insulating oil meeting the qualifications of ASTM D3487-00 is received in the field for installation in LTCs, it should be checked for certain key values that may be affected by shipment and storage (see Table 1). Viscosity [12 cSt (12 m^2/s) maximum at 40 °C] and pour point (–40 °C, maximum) should be checked in cold climates (below –25 °C and above –40 °C) to ensure that the oil does not interfere with the free operation of the equipment.

9.2.3 New oil properties—oil shipped in new equipment

LTCs are normally shipped from the factory without oil. If an LTC is filled with oil prior to shipping, refer to Table 11.

9.2.4 New oil properties—prior to energizing

When mineral insulating oil is received in bulk shipping containers, it is processed according to the instructions of the transformer manufacturer and then introduced into the equipment. Table 11 gives test limits for LTC mineral insulating oil after being processed, placed in equipment, and allowing for standing time before energizing.

9.2.5 Service-aged oil properties

Suggested limits for continued use of service-aged LTC oils are shown in Table 12.

9.3 Reconditioning

If the dielectric strength of the oil drops below the values given in Table 12, or the water content exceeds the values given in Table 12, the oil should be reconditioned or changed.

Copyright © 2002 IEEE. All rights reserved.

Copyright The Institute of Electrical and Electronics Engineers, Inc.
Provided by IHS under license with IEEE
No reproduction or networking permitted without license from IHS Not for Resale

Table 11—Test limits of new mineral insulating oil for load tap changers, prior to energizing

Test and method	Suggested limit
Dielectric strength, ASTM D1816-97, kV minimum, 1 mm, gap[a] 2 mm, gap[a]	 35 55
Water content, ASTM Dl533-00, mg/kg maximum[b]	 10
Corrosive sulfur, ASTM D1275-96a	No corrosive sulfur in oil.

[a]Alternate measurements of 0.04 in and 0.08 in respectively for gaps.
[b]Equivalent measurement is parts per million, ppm.

Table 12—Limits for continued use of service-aged insulating oil for load tap changers

Test and method	Suggested limit		
	Neutral end	Line end	
		≤ 69 kV	> 69 kV
Dielectric strength, ASTM D1816-97, kV minimum, 1 mm, gap[a] 2 mm, gap[a]	 20 27	 25 35	 28 45
Water content, ASTM Dl533-00, mg/kg maximum[b]	 40	 30	 25
Corrosive sulfur, ASTM D1275-96a	No corrosive sulfur in oil.		

[a]Alternate measurements of 0.04 in and 0.08 in respectively for gaps.
[b]Equivalent measurement is parts per million, ppm.

10. Health and environmental care procedures for mineral insulating oil

10.1 Health issues

Users should obtain a Material Safety Data Sheet (MSDS) for each dielectric fluid in use. Where instructions differ from recommendations made here, the instructions of the manufacturer are to be followed. Although there is no special risk involved in the normal handling of insulating fluids addressed in this guide, attention should be focused to the general need for personal hygiene or the practice of washing skin and clothing that may have come in contact with insulating oil. Personnel should avoid contact of the fluid with their eyes. When dielectric liquids have to be disposed of, certain precautions are necessary to comply with local, state, and federal requirements in the United States. These oils are generally classified as special, regulated or hazardous waste depending upon the individual state. The following procedures are not intended to supersede local, state, or federal regulations.

Copyright © 2002 IEEE. All rights reserved.

Copyright The Institute of Electrical and Electronics Engineers, Inc.
Provided by IHS under license with IEEE
No reproduction or networking permitted without license from IHS
Not for Resale

Unless a PCB analysis has been performed, it is prudent to assume that the batch of oil contains PCBs and to act accordingly. The absence of PCBs in a volume of oil in or from a piece of equipment can be established only by analysis of that oil.

10.2 Leaks and spills

During equipment inspection or servicing, routine checks should be made of the equipment and surroundings for leaks. Areas to check and repair should include valves, bushings, gauges, tap changers, welds, sample ports, manhole covers, pipe fittings, pressure relief valves, etc. The user is referred to IEEE Std 980-1994.

New transformer oil as received from a refiner is very unlikely to contain PCBs. However, many older transformers and other pieces of electrical equipment in service are filled with mineral insulating oil that contains PCBs. Since 1977, various federal, state, and local environmental regulations have governed the handling and processing of mineral oils containing PCBs. While these regulations can add substantially to the complexity of spill cleanup and disposal of oils, they should not be disregarded.

10.2.1 Minor spills

Minor spills, such as those occurring in the manufacture or repair of equipment, can be cleaned using absorbent rags or other materials.

10.2.2 Spills on soil

Soil acts as an absorbent and should not be allowed to become saturated with mineral insulating oil. Users should consult the applicable local, state, and federal guidelines in the United States for spills of mineral oil onto soil and the remedies available. Depending on state and local regulations, spills to soil may have to be reported to one or more regulatory agencies.

10.2.3 Spills on water

Because mineral insulating oils float on water, a spill can be contained by using floating booms or dikes. Section 311 of the Federal Water Pollution Control Act as amended, 33 U.S.C. 1251 *et seq*, also known as the Clean Water Act as found in Title 40 Code of Federal Regulations Part 110, imposes reporting requirements for petroleum oils that are spilled into navigable water ways. The requirement to report is triggered by the appearance of a sheen on the surface of the water. If a sheen is noted, the U. S. Coast Guard must be notified, as well as the National Response Center.

Once the mineral oil has been concentrated, it can be removed from the surface of the water by systems that are normally used for petroleum spills. These include pumps, skimmers, physical absorbents, and fibers that are fabricated into floating ropes.

NOTE—If spilled mineral insulating oils are known or assumed to contain any concentration of PCBs, they must be treated as a PCB containing liquid. Also refer to the Spill Policy Guide of the Environmental Protection Agency (see PCBs 761.120, Title 40 Code of Federal Regulations Part 761).

Copyright © 2002 IEEE. All rights reserved.

Copyright The Institute of Electrical and Electronics Engineers, Inc.
Provided by IHS under license with IEEE
No reproduction or networking permitted without license from IHS
Not for Resale

Annex A

(informative)

Bibliography

[B1] Bruce, C. M., Christie, J. D., and Griffen, Paul, 55th Annual Conference of Doble Clients—1988 Ed., Section 10-9.1.

[B2] IEEE Std C57.12.90-1999, IEEE Standard Test Code for Liquid-Immersed Distribution, Power, and Regulating Transformers.

Copyright © 2002 IEEE. All rights reserved.

Copyright The Institute of Electrical and Electronics Engineers, Inc.
Provided by IHS under license with IEEE
No reproduction or networking permitted without license from IHS
Not for Resale