TC 15-86 6470247 0004285 8 A-07-11

NEMA STANDARDS PUBLICATION/NO. TC 15

nema

Corrugated Polyvinyl Chloride (PVC) Fiber Optic Innerduct

NEMA

NATIONAL ELECTRICAL MANUFACTURERS ASSOCIATION ■ 2101 L STREET N.W., WASHINGTON, D.C. 20037

Copyright National Electrical Manufacturers Association
Provided by IHS under license with NEMA
No reproduction or networking permitted without license from IHS

Not for Resale

NEMA TC 15-1986

TC 15

CORRUGATED POLYVINYL CHLORIDE (PVC) FIBER OPTIC INNERDUCT

Published by

National Electrical Manufacturers Association
2101 L St. N.W.
Washington, DC 20037
(202) 457-8400

©1986 by National Electrical Manufacturers Association

Copyright National Electrical Manufacturers Association
Provided by IHS under license with NEMA
No reproduction or networking permitted without license from IHS
Not for Resale

CORRUGATED PVC FIBER OPTIC INNERDUCT

TABLE OF CONTENTS

Page

FOREWORD i
SCOPE ii

Section 1 REFERENCED STANDARDS AND DEFINITIONS
Referenced Standards 1
Definitions and Abbreviations 1

Section 2 APPLICATIONS, MATERIALS, AND SIZE
Applications 2
Materials 2
Dimensions 2
Workmanship 2

Section 3 PERFORMANCE REQUIREMENTS
Flattening 3
Impact Resistance 3
Resistance to Mechanical Abuse 3
Tension Test 3
Flammability 4

Section 4 TEST METHODS
Conditioning, Test Conditions, and Sampling 4
Dimensions 4
Flattening 4
Impact Resistance 4
Resistance to Mechanical Abuse 5
Tension Test 5
Flammability 5

LIST OF TABLES
Table 2-1 Dimensions 2
Table 3-1 Drop Height For Impact Resistance 3
Table 3-2 Tension Force Requirements 4

Copyright National Electrical Manufacturers Association
Provided by IHS under license with NEMA
No reproduction or networking permitted without license from IHS
Not for Resale

FOREWORD

In the preparation of this Standards Publication, input of users, and other interested parties has been sought and evaluated. Inquiries, comments, and proposed or recommended revisions should be submitted to the Plastic Conduit, Duct, and Accessories Section by contacting:

Manager, Engineering Department
National Electrical Manufacturers Association
2101 L Street, N.W.
Washington, D.C. 20037

The purpose of these standards for corrugated PVC fiber optic innerduct is:

1. To list dimensions and other significant requirements.
2. To set forth some of the properties of these products and to assist in selecting and obtaining the proper product for a particular need.

Copyright National Electrical Manufacturers Association
Provided by IHS under license with NEMA
No reproduction or networking permitted without license from IHS
Not for Resale

SCOPE

These standards cover corrugated PVC innerduct designed to be used as protection for fiber optic cable, and other conductors within larger raceways, cable trays, or similar enclosures.

Copyright National Electrical Manufacturers Association
Provided by IHS under license with NEMA
No reproduction or networking permitted without license from IHS
Not for Resale

CORRUGATED PVC FIBER OPTIC INNERDUCT

Section 1

REFERENCED STANDARDS AND DEFINITIONS

1.1 REFERENCED STANDARDS

In this publication, reference is made to the following publications. Copies are available from the sources indicated.

American Society for Testing and Materials
1916 Race Street
Philadelphia, PA 19103

D 618-61 (1981)	*Conditioning Plastics and Electrical Insulating Materials for Testing*
D 883-83	*Definition of Terms Relating to Plastics*
D 1600-83	*Abbreviations of Terms Relating to Plastics*
D 1784-81	*Specification for Rigid Poly(vinyl Chloride) Compounds and Chlorinated Poly(vinyl Chloride) Compounds*
D 2122-81	*Determining Dimensions of Thermoplastic Pipe and Fittings*
D 2444-84	*Standard Test Method for Impact Resistance of Thermoplastic Pipe and Fittings by means of a Tup (Falling weight)*

NEMA Standard 5-19-1986.

F-412-82a	*Definitions of Terms Relating to Plastic Piping Systems*

Underwriters Laboratories Inc.
333 Pfingsten Road
Northbrook, IL 60062

ANSI/UL 651-1980 Rigid Nonmetallic Conduit

1.2 DEFINITIONS AND ABBREVIATIONS

Corrugated PVC fiber optic innerduct is a rigid polyvinyl chloride (PVC) corrugated raceway of circular cross-section intended for the installation of optic fiber cable within a larger conduit system. Other definitions of terms shall be in accordance with ASTM D-883 or ASTM F-412. Abbreviations shall be in accordance with ASTM D-1600 unless otherwise indicated. The values stated in U.S. customary units are to be regarded as the standard.

NEMA Standard 5-19-1986.

Copyright National Electrical Manufacturers Association
Provided by IHS under license with NEMA
No reproduction or networking permitted without license from IHS
Not for Resale

Section 2

APPLICATIONS, MATERIALS, AND SIZE

2.1 APPLICATIONS

Corrugated PVC fiber optic innerduct is designed to provide individual raceways within a conduit system designed to contain several fiber optic cables. Individual raceways allow maximum utilization of the larger conduit while preventing damage to new or existing cable(s) during cable installation or removal activities. Corrugated PVC fiber optic innerduct can also be used above ground providing it is not subject to, or is given protection from, physical damage. Corrugated PVC fiber optic innerduct should not be used:

1. For support of fixtures or other equipment;
2. Where subject to physical damage.

Authorized Engineering Information 5-19-1986.

2.2 MATERIALS

Corrugated PVC fiber optic innerduct shall be made from polyvinyl chloride (PVC) compounds which meet the cell classification PVC 12233 A, B or C as defined in ASTM D-1784. Other homopolymer PVC compounds that have different cell classification, because one or more properties are superior to those compounds specified above, shall also be permitted. Use of rework material shall be permitted provided the innerducts produced meet all the requirements of these standards.

NEMA Standard 5-19-1986.

2.3 DIMENSIONS

The dimensions of corrugated PVC fiber optic innerduct shall meet the requirements of Table 2-1 when determined accordance with ASTM D-2122.

NEMA Standard 5-19-1986.

2.4 WORKMANSHIP

Corrugated PVC fiber optic innerduct shall be homogeneous throughout, free from visible cracks, holes, foreign inclusions, and other defects.

NEMA Standard 5-19-1986.

Table 2-1
DIMENSIONS

Inches (Millimeters)

Nominal Size Inches	Outside Dia. Avg.	Out of Roundness Max.	Out of Roundness Min.	Inside Dia. Min.
1	1.315 ± .008	1.325	1.305	1.00
	(33.4 ± .20)	(33.66)	(33.15)	(25.4)
1-1/4	1.660 ± .008	1.672	1.648	1.33
	42.16 ± .20	(42.47)	(41.86)	(33.8)
1-1/2	1.900 ± .008	1.912	1.888	1.56
	48.26 ± .2	(48.56)	(47.96)	39.6

Copyright National Electrical Manufacturers Association
Provided by IHS under license with NEMA
No reproduction or networking permitted without license from IHS
Not for Resale

Section 3

PERFORMANCE REQUIREMENTS

3.1 FLATTENING

There shall be no evidence of splitting, cracking, or breaking when corrugated PVC fiber optic innerduct is tested in accordance with 4.3.

Retest—Because of failure that can be introduced by sample preparation and test procedure, if one specimen fails the original test, two additional sets of three specimens shall be tested. Both sets tested on retest must meet the requirements of this standard.

NEMA Standard 5-19-1986.

3.2 IMPACT RESISTANCE

No crack or tear longer than 1/32 inch (.79 mm) shall appear in seven out of ten specimens of corrugated PVC fiber optic innerduct when tested in accordance with 4.4 using the values given in Table 3-1.

Retest—Because of failures that can be introduced by sample preparation and test procedure, if initial test fails, two additional sets of specimens shall be tested. Both sets tested on retest must meet the requirements of this standard.

NEMA Standard 5-19-1986.

3.3 RESISTANCE TO MECHANICAL ABUSE

There shall be no evidence of cracking or opening of any kind when corrugated PVC fiber optic innerduct is tested according to both Method 1 and Method 2 of 4.5.

Retest—Because of failure that can be introduced by sample preparation and test procedure, if initial test fails, two additional sets of specimens shall be tested. Both sets tested on retest must meet the requirements of this standard.

NEMA Standard 5-19-1986.

3.4 TENSION TEST

The corrugated PVC fiber optic innerduct shall withstand application of the tension force given in Table 3-2 when tested in accordance with 4.6.

Retest—Because of failure than be introduced by sample preparation a test procedure, if initial test fails, two additional sets of specimens shall be tested. Both sets tested on retest must meet the requirements of this standard.

NEMA Standard 5-19-1986.

Table 3-1
DROP HEIGHT FOR IMPACT RESISTANCE

Nominal Size Inches	Height of the Space Between the Bottom of the Weight and the Top of the Specimen Before the Weight is Released	
	ft.	m
1	2	.61
1-1/4	2.5	.76
1-1/2	3.0	.91

Copyright National Electrical Manufacturers Association
Provided by IHS under license with NEMA
No reproduction or networking permitted without license from IHS
Not for Resale

Table 3-2
TENSION FORCE REQUIREMENTS

Nominal Size, Inches	Tension Force, lbs. (kg)
1″	490
1-1/4″	560
1-1/2″	610

3.5 FLAMMABILITY

The corrugated PVC fiber optic innerduct shall meet the following requirement when tested in accordance with 4.7:

The corrugated PVC fiber optic innerduct shall have no flaming or glowing particle drop or fall from the specimen. Tubing shall not continue to flame longer than five seconds after removal of flame. The tubing shall not be completely consumed during or after the application of flame.

NEMA Standard 5-19-1986.

Section 4

TEST METHODS

4.1 CONDITIONING, TEST CONDITIONS, AND SAMPLING

4.1.1 Conditioning Test Specimens

When conditioning is required, the test specimens shall be conditioned in accordance with Procedure A in ASTM D-618 at 73.4±23.6°F (23±2°C) and 50±2 percent relative humidity for not less than 40 hours prior to the test unless otherwise specified.

NEMA Standard 5-19-1986.

4.1.2 Test Conditions

Tests shall be conducted at 73.4± 3.6°F (23± 2°C) and 50±2 percent relative humidity unless otherwise specified.

NEMA Standard 5-19-1986.

4.1.3 Sampling

Samples shall be selected at random.

NEMA Standard 5-19-1986.

4.2 DIMENSIONS

4.2.1 Outside Diameter (Out-of-Roundness)

The outside diameter of corrugated PVC fiber optic innerduct shall be measured in accordance with Section 9 of ASTM D-2122. Out-of-roundness tolerance shall apply only at the point of manufacture.

NEMA Standard 5-19-1986.

4.2.2 Outside Diameter (Average)

The average outside diameter at any cross section on the length of corrugated PVC fiber optic innerduct shall be determined in accordance with Section 9 of ASTM D-2122 or as measured by the use of a vernier circumferential tape in accordance with Section 9 of ASTM D-2122.

NEMA Standard 5-19-1986.

4.3 FLATTENING

Three 2-inch (50.8 mm) long specimens shall be flattened between parallel plates in a suitable press until the distance between the plates is 40 percent of the outside diameter of the product. The rate of loading shall be uniform and such that the compression is completed within 2 to 5 minutes. On removal of the load, the specimen shall be examined for evidence of splitting, cracking, or breaking.

NEMA Standard 5-19-1986.

4.4 IMPACT RESISTANCE

Ten 6-inch (152 mm) long specimens, on the surface of which there are no cracks, tears, or other imperfections shall be cut from each nominal size of corrugated PVC fiber optic innerduct. The specimens shall be tested separately while resting on a solid flat steel plate which is at least 1/2 inch (13 mm) thick and which is firmly anchored with its upper surface horizontal. A 20-lb. (9.07 kg) "B" Tup, as described in ASTM D-2444, shall be allowed to fall freely through a vertical guide from the height indicated in Table 3-2. The force of the weight shall strike the center of the specimen once; provision shall be

Copyright National Electrical Manufacturers Association
Provided by IHS under license with NEMA
No reproduction or networking permitted without license from IHS
Not for Resale

made to prevent the weight from striking the specimen more than once. The conditioning time for impact specimens shall be a minimum of 1 hour 74.4±3.6°F (23° 2°C). The specimen shall be examined for breaks or splits.

NEMA Standard 5-19-1986.

4.5 RESISTANCE TO MECHANICAL ABUSE

This test is conducted to determine the resistance of corrugated PVC fiber optic innerduct to abnormal conditions of excessive bending which might possibly occur in use. The ability of corrugated PVC fiber optic innerduct to be bent around a mandrel without cracking at any point shall be evaluated in accordance with 4.5.1 and 4.5.2.

NEMA Standard 5-19-1986.

4.5.1 Test Method 1

After condition 1 hour at 73.4°±3.6°F (23°±2°C), three samples of each nominal size (1″, 1-1/4″, and 1-1/2″) of corrugated PVC fiber optic innerduct shall be bent around a mandrel 360 degrees at a room ambient temperature 73.4°±3.6°F (23°±2°C). The radius of the mandrel around which the samples shall be bent is as follows:

Nominal Size Inches	Radius of Mandrel Inches(mm)
1″	5.0 (127)
1-1/4″	7.0 (177.8)
1-1/2″	8.0 (203.2)

Tension shall be applied at a uniform rate to the specimen under test as necessary to cause the corrugated PVC fiber optic innerduct to conform closely to the curved surface. While in this position, each specimen shall be examined carefully for any breaks.

NEMA Standard 5-19-1986.

4.5.2 Test Method 2

Three samples of each nominal size of corrugated PVC fiber optic innerduct shall be conditioned at a temperature 32°F (0°C) for a period of five hours. The specimens shall be removed from the cold chamber one at a time and immediately bent halfway (180 degrees) around the mandrel used for Method 1. Tension shall be applied at a uniform rate to each specimen as necessary to cause the corrugated PVC fiber optic innerduct to conform closely to the curved surface. While in this position, the specimen shall be examined carefully for evidence of cracking.

NEMA Standard 5-19-1986.

4.6 TENSION TEST

Six specimens 21 inches (533 mm) long shall be cut from sample lengths. The ends of each specimen are to be smooth and perpendicular to the longitudinal axis of the tubing. A grip shall be fitted to each end of the specimen. If needed to support the tubing, a smooth plug shall be placed inside the tubing under the grip and up to one inch beyond the grip. The specimens are than connected and the load smoothly applied and maintained for one minute without the tubing breaking.

NEMA Standard 5-19-1986.

4.7 FLAMMABILITY

Three samples of each size of corrugated PVC fiber optic innerduct shall be subjected to and shall meet the requirements of the flammability test in UL 651.

NEMA Standard 5-19-1986.

Copyright National Electrical Manufacturers Association
Provided by IHS under license with NEMA
No reproduction or networking permitted without license from IHS
Not for Resale

September 1984

NEMA STANDARDIZATION

The purpose of NEMA Standards, their classification and status are set forth in certain clauses of the NEMA Bylaws, which are quoted below:

Purpose of Standards

National Electrical Manufacturers Association Standards are adopted in the public interest and are designed to eliminate misunderstandings between the manufacturer and the purchaser and to assist the purchaser in selecting and obtaining the proper product for its particular need. Existence of a National Electrical Manufacturers Association Standard does not in any respect preclude any member or nonmember from manufacturing or selling products not conforming to the standard.

(Bylaw—Art. V, Sec. 1)

Definition of a Standard

A standard of the National Electrical Manufacturers Association defines a product, process or procedure with reference to one or more of the following: nomenclature, composition, construction, dimensions, tolerances, safety, operating characteristics, performance, rating, testing, and the service for which they are designed.

(Bylaw—Art. V, Sec. 2, Subsection A)

Dimensions

Where dimensions are given for interchangeability purposes, alternate dimensions satisfying the other provisions of the standards publication may be capable of otherwise equivalent performance.

(NEMA Policy Memorandum 84-2, dated June 7, 1984)

Classes of Standards

National Electrical Manufacturers Association Standards are of two classes:

1. NEMA Standard, which relates to a product commercially standardized and subject to repetitive manufacture, which standard has been approved by at least 90 percent of the members of the Subdivision eligible to vote thereon;
2. Suggested Standard for Future Design, which may not have been regularly applied to a commercial product, but which suggests a sound engineering approach to future development, which standard has been approved by at least two-thirds of the members of the Subdivision eligible to vote thereon.

(Bylaw—Art. V, Sec. 2, Subsection B)

Authorized Engineering Information

Authorized Engineering Information consists of explanatory data and other engineering information of an informative character not falling within the classification of NEMA Standard or Suggested Standard for Future Design.

(Bylaw—Art. V, Sec. 6, 1st Sentence)

Official Standards Proposal

An Official Standards Proposal is an official draft of a proposed standard which is formally recommended to an outside organization(s) for consideration, comment and/or approval.

(Bylaw—Art. V, Sec. 4, Subsection A)

Identification of Status

Standards in NEMA Standards Publications are identified in the foreword or following each standard as "NEMA Standard" or "Suggested Standard for Future Design." These indicate the status of the standard. These words are followed by a date which indicates when the standard was adopted in its present form by the Association.

The material identified as "Authorized Engineering Information" and "Official Standards Proposal" is designated similarly.

Copyright National Electrical Manufacturers Association
Provided by IHS under license with NEMA
No reproduction or networking permitted without license from IHS
Not for Resale

PLASTIC CONDUIT, DUCT, AND ACCESSORIES SECTION

MEMBER COMPANIES

Can-Tex Industries
Mineral Wells, TX 76067

Carlon
Div. Electrical Sciences Inc.
Cleveland, OH 44122

Certainteed Corporation
Valley Forge, PA 19482

Challenger Electrical Materials
Inc.
Parkersburg, WV 26101

Formex Manufacturing, Inc.
Atlanta, GA 30362

Highland Plastics Inc.
Newburgh, NY 12550

Harvey Hubbell, Inc.
Kellems Div.
Stonington, CT 06378

Kock Fiberglass Products Co.
Wichita, KS 67217

Midwest Plastic Fabricators, Inc.
Chagrin Falls, OH 44022

NVF Company
Fiberglass Tubular Division
Houston, TX 77038

Robroy Industries, Inc.
Verona, PA 15147

Thomas & Betts Corporation
Raritan, NJ 08869

Underground Devices, Inc.
Glenview, IL 60025

Underground Products, Inc.
Troy, MI 48099-3230

Copyright National Electrical Manufacturers Association
Provided by IHS under license with NEMA
No reproduction or networking permitted without license from IHS
Not for Resale