9009279 0002589 698

NEMA STANDARDS PUBLICATION/NO. TC 5-1983

nema

# Corrugated Polyolefin Coilable Plastic Utilities Duct

NEMA

NATIONAL ELECTRICAL MANUFACTURERS ASSOCIATION ■ 2101 L STREET, N.W., WASHINGTON, D.C. 20037

Copyright National Electrical Manufacturers Association
Provided by IHS under license with NEMA
No reproduction or networking permitted without license from IHS

Not for Resale

# TABLE OF CONTENTS


| | | Page |
|---|---|---|
| | FOREWORD | i |
| | SCOPE | ii |
| **Section 1** | Referenced Standards | 1 |
| **Section 2** | GENERAL | |
| | Definitions | 2 |
| | Nominal Sizes | 2 |
| **Section 3** | MATERIALS, DIMENSIONS, AND WORKMANSHIP | |
| | Materials | 3 |
| | Dimensions | 3 |
| | Workmanship | 3 |
| | Factory-Made Joints | 3 |
| **Section 4** | PERFORMANCE TESTS | |
| | Conditioning Test Specimens | 4 |
| | Test Conditions | 4 |
| | Duct Stiffness | 4 |
| | Compression and Recovery | 4 |
| | Impact Test | 4 |
| | Low Temperature Handling Test | 4 |
| | Axial Pull Test on Factory-Made Joints | 5 |
| **Section 5** | INSTALLATION | |
| | Installation Procedures | 6 |
| **Section 6** | MARKING | |
| | Marking | 6 |
| **Appendix A** | INSTALLATION PRACTICES | 6 |


© 1984 by National Electrical Manufacturers Association

Copyright National Electrical Manufacturers Association
Provided by IHS under license with NEMA
No reproduction or networking permitted without license from IHS
Not for Resale

## Foreword

The purpose of these standards for corrugated polyolefin coilable plastic utilities duct for underground use is:

1. To define dimensions and other significant requirements.
2. To inform producers, distributors, engineers, code officials, and users about some of the properties of these products and to assist in selecting and obtaining the proper product for a particular need.

User needs have been considered throughout the development of these standards. Test methods and performance values have been related as closely as possible to end-use applications.

The Plastic Conduit, Duct and Accessories Section of NEMA, through its members, has worked (and continues to work) closely with such organizations as the American Society for Testing and Materials, the Plastic Pipe Institute, appropriate government agencies, and others in the periodic review and revision of these standards for any changes necessary to keep them up to date with advancing technology. Proposed or recommended revisions should be submitted to:

Manager, Engineering Department
National Electrical Manufacturers Association
2101 L Street, N.W.
Washington, D.C. 20037

Publication No. TC 5-1983 revises and supersedes the NEMA Standards Publication for *Corrugated Polyolefin Coilable Plastic Utilities Duct,* Publication No. TC 5-1978. Prior to publication, the NEMA Standards, Suggested Standards for Future Design, and Authorized Engineering Information which appear in this publication unchanged since their appearance in TC 5-1978 were reaffirmed.

## Scope

These standards cover requirements and methods of tests for materials, dimensions, workmanship, and so forth, of corrugated polyolefin coilable electrical plastic duct intended for the installation of cables or wires either in the factory or in the field.

NOTE—The values stated in U.S. customary units are to be regarded as the standard.



Copyright National Electrical Manufacturers Association
Provided by IHS under license with NEMA
No reproduction or networking permitted without license from IHS
Not for Resale

# CORRUGATED POLYOLEFIN COILABLE PLASTIC UTILITIES DUCT

## Section 1
## REFERENCED STANDARDS

In this publication, reference is made to the following standards and other publications listed below. Copies are available from the indicated sources.

**American Society for Testing and Materials**
1916 Race Street
Philadelphia, PA 19103

| | |
|---|---|
| D 618-81 | *Conditioning Plastics and Electrical Insulating Materials for Testing* |
| D 1238-82 | *Measuring Flow Rates of Thermoplastics by Extrusion Plastometer* |
| D 1248-81a | *Specifications for Polyethylene Plastics Molding and Extrusion Materials* |
| D 1693-80 | *Test for Environmental Stress-cracking of Ethylene Plastics* |
| D 2146-82 | *Specifications for Propylene Plastic Molding and Extrusion Materials* |
| D 2412-77 | *Test for External Loading Properties of Plastic Pipe by Parallel-plate Loading* |
| D 2444-80 | *Test for Impact Resistance of Thermoplastic Pipe and Fittings by Means of a Tup (Falling Weight)* |
| D 1600-81 | *Plastics, Abbreviations of Terms Relating to* |
| D 883-80c(1982) | *Plastics, Definitions of Terms Relating to* |
| F 412-82a | *Definitions of Terms Related to Plastic Piping Systems* |

**National Electrical Manufacturers Association**
2101 L Street, N.W.
Washington, D.C. 20037

| | |
|---|---|
| Bulletin No. TCB3-1976 | *User's Manual for the Installation of Underground Corrugated Coilable Plastic Utility Duct (CCD)* |

Copyright National Electrical Manufacturers Association
Provided by IHS under license with NEMA
No reproduction or networking permitted without license from IHS
Not for Resale

# Section 2
# GENERAL

## 2.1 DEFINITIONS

Corrugated polyolefin coilable plastic utilities duct is a plastic duct which is intended for underground use and which can be manufactured and coiled or reeled in continuous transportable lengths and uncoiled for further processing or installation or both, without adversely affecting its properties or performance. NEMA Standard 5-20-1974.

## 2.2 NOMINAL SIZES

The nominal sizes of coilable plastic duct shall be 1¼, 1½, 2, 2½, 3, 3½, 4, and 5 inches.

NEMA Standard 5-20-1974.

Copyright National Electrical Manufacturers Association
Provided by IHS under license with NEMA
No reproduction or networking permitted without license from IHS

Not for Resale

# Section 3
# MATERIALS, DIMENSIONS, AND WORKMANSHIP

## 3.1 MATERIALS

The duct shall be manufactured from one of the following polyolefins:

1. High-density polyethylene.
2. Copolymer polypropylene.

The high-density polyethylene shall meet the requirements given in ASTM D 1248, Type III, Class C, and, in addition, shall have a maximum melt index of 0.50 when tested in accordance with ASTM D 1238, Condition E, and an environmental stress crack resistance of zero failures in 24 hours when tested in accordance with ASTM D 1693, Condition B.

The polypropylene shall meet the requirements given in ASTM D 2146, Type II, and shall contain at least 1 percent carbon black or ultraviolet stabilizers, or both. In addition, it shall have an environmental stress crack resistance of zero failures in 1000 hours when tested in accordance with ASTM D 1693, Condition B.

Reworked material may be used provided that the duct produced meets all of the requirements of these standards.

NEMA Standard 5-20-1974.

## 3.2 DIMENSIONS

Coilable plastic duct shall have the dimensions shown in Table 3-1.

NEMA Standard 5-20-1974.

**Table 3-1**
**DIMENSIONS**

| Nominal Size, Inches | Minimum Inside Diameter in(mm) | Minimum Bend Radius* in(mm) | Minimum Wall Thickness in(mm) |
|---|---|---|---|
| 1¼ | 1.44 (36.6) | 7(178) | 0.020(0.51) |
| 1½ | 1.65 (41.9) | 8(203) | 0.020(0.51) |
| 2 | 2.00 (50.8) | 9(229) | 0.020(0.51) |
| 2½ | 2.50 (63.5) | 10(254) | 0.020(0.51) |
| 3 | 2.95 (74.9) | 13(330) | 0.020(0.51) |
| 3½ | 3.45 (87.6) | 14(356) | 0.020(0.51) |
| 4 | 3.95 (100.3) | 16(406) | 0.020(0.51) |
| 5 | 4.95 (125.7) | 20(508) | 0.020(0.51) |

*Applies to the duct. The type of the cable to be used will determine actual minimum bend radius as installed.

## 3.3 WORKMANSHIP

Coilable plastic duct shall be homogeneous throughout and free from visible cracks, holes, foreign inclusions, or other defects. It shall be as uniform as practicable in color, opacity, density, and other physical properties.

NEMA Standard 5-17-1971.

## 3.4 FACTORY-MADE JOINTS

One factory-made joint per 500 feet (152 m) of duct may be made provided the product meets the performance requirements of these standards.

NEMA Standard 3-8-1978.

Copyright National Electrical Manufacturers Association
Provided by IHS under license with NEMA
No reproduction or networking permitted without license from IHS
Not for Resale

# Section 4
# PERFORMANCE TESTS

## 4.1 CONDITIONING TEST SPECIMENS

When conditioning is required, the test specimen shall be conditioned in accordance with Procedure A in ASTM D 618 at 73.4° ± 3.6°F(23° ± 2°C) and 50 ± 5 percent relative humidity for not less than 48 hours prior to the test unless otherwise specified.

NEMA Standard 3-8-1978.

## 4.2 TEST CONDITIONS

Tests shall be conducted at 73.4° ± 3.6°F (23° ± 2°C) and 50 ± 5 percent relative humidity unless otherwise specified.

NEMA Standard 3-8-1978.

## 4.3 DUCT STIFFNESS

Three 6-in (152 mm) long specimens conditioned in accordance with 4.1 shall be tested using the apparatus described in ASTM D 2412. The specimens shall be compressed at the rate of ½ in (13 mm) per minute and the load recorded at the vertical deflection equivalent to 5 percent of the original inside diameter of the specimen.

The duct stiffness at 5 percent vertical deflection shall be determined as follows:

$$\text{Duct Stiffness, psi} = \frac{F}{Y}$$

Where:

F = Load pounds per inch (kilograms per 25.4 millimeters) of length recorded at 5 percent vertical deflection in inches (millimeters).

Y = Vertical deflection of inside diameter in inches (millimeters).

The minimum duct stiffness shall be 130 psi (897.3 kPa).

NEMA Standard 3-8-1978.

## 4.4 COMPRESSION AND RECOVERY

Three 6-in (152 mm) long specimens conditioned in accordance with 4.1 shall be tested using the apparatus described in ASTM D 2412. The specimens shall be compressed at the rate of ½ in (13 mm) per minute until the distance between the plates has been decreased by 50 percent of the original inside diameter of the duct. When the load is removed, the specimens shall recover to at least 80 percent of their original diameter within 10 minutes.

There shall be no evidence of splitting or cracking of any of the specimens.

NEMA Standard 3-8-1978.

## 4.5 IMPACT TEST

### 4.5.1 Room Temperature Test

Ten 6-in (152 mm) specimens on the surfaces of which there are no cracks, tears, or other imperfections shall be cut from finished lengths of each size of coilable plastic duct to be tested. The specimens, the test apparatus, and the surrounding air shall be in thermal equilibrium with one another at a temperature of 73.4° ± 3.6°F (23° ± 2°C) during the test. The test apparatus and method shall be as described in 4.5.3.

### 4.5.2 Low Temperature Test

Ten 6-in (152 mm) specimens on the surface of which there are no cracks, tears, or other imperfections shall be cut from finished lengths of each size of coilable plastic duct to be tested. The specimens shall then be conditioned at a temperature of 32° ± 3.6°F (0° ± 2°C) for 5 hours. The test apparatus shall be at a room temperature of 73.4° ± 3.6°F (23° ± 2°C). The samples shall be removed from the cold chamber and immediately tested for impact in accordance with 4.5.3. The time between removal of the sample from the cold chamber and completion of impact shall not exceed 15 seconds.

### 4.5.3 Test Method

The specimens shall be tested in accordance with ASTM D 2444, using a 20-lb (9 kg) tup B and flat plate holder B.

The minimum impact strength shall be in accordance with Table 4-1. The duct does not meet the requirements of this standard if a crack or tear longer than 1/32 in (0.8 mm) appears on the outer surface of more than three of the ten specimens.

## 4.6 LOW TEMPERATURE HANDLING TEST

Ten 30-in (762 mm) specimens shall be conditioned at a temperature of −4° ± 3.6°F (−20° ± 2°C) for 5 hours. The specimens shall be removed from the cold chamber and each one of them shall be dropped from a height of about 5 ft (1.5 m) onto a concrete floor twice in quick succession. During the first drop, the specimen shall make an angle of approximately 45° with the floor so that one

Copyright National Electrical Manufacturers Association
Provided by IHS under license with NEMA
No reproduction or networking permitted without license from IHS
Not for Resale

**Table 4-1**
**MINIMUM IMPACT STRENGTH**

| Nominal Size, Inches | Height of the Face of the Weight Above the Specimen Before the Weight is Released | |
|---|---|---|
| | Room-temperature Test 73.4°F (23°C) | Low-temperature Test −4°F (−20°C) |
| | ft (m) | ft (m) |
| 1¼ | 1½ (0.46) | ¾ (0.23) |
| 1½ | 1½ (0.46) | ¾ (0.23) |
| 2 | 2 (0.61) | 1 (0.30) |
| 2½ | 2 (0.61) | 1 (0.30) |
| 3 | 4 (1.22) | 2 (0.61) |
| 3½ | 6 (1.83) | 3 (0.91) |
| 4 | 6 (1.83) | 3 (0.91) |
| 5 | 6 (1.83) | 3 (0.91) |

NEMA Standard 3-8-1978.

end of it reaches the floor first. During the second drop, the specimen shall fall parallel to the floor.

Right after the drop test, each specimen shall be bent to the appropriate bending radii shown in Table 3-1.

The duct does not meet the requirements of this standard if it shatters or chips, or if a crack or tear longer than 1/32 in (0.8 mm) appears on the outer surface of more than three of the ten specimens.

NEMA Standard 3-8-1978.

## 4.7 AXIAL PULL TEST ON FACTORY-MADE JOINTS

Two 18-in (457 mm) lengths of each size of duct shall be joined using the manufacturer's recommended procedure. A static axial load of 60 lb (27 kg) shall be applied to each joint for 5 minutes.

The joint shall not become separated or damaged.

NEMA Standard 3-8-1978.

Copyright National Electrical Manufacturers Association
Provided by IHS under license with NEMA
No reproduction or networking permitted without license from IHS

Not for Resale

# Section 5
# INSTALLATION

## 5.1 INSTALLATION PROCEDURES

For proper installation, refer to procedures recommended by the manufacturer.

Authorized Engineering Information 5-17-1971.

# Section 6
# MARKING

## 6.1 MARKING

Each length of duct shall be clearly and durably marked at least every 10 ft (3 m) with the material designation (HDPE for high-density polyethylene or PP for polypropylene), nominal size of the duct, and with the name and/or trademark of the manufacturer.

NOTE—The marking may be shown on the packaging instead of on the duct.

NEMA Standard 3-8-1978.

# Appendix A
# INSTALLATION PRACTICES

It is recommended that the products described by these standards be installed in accordance with the applicable parts of NEMA Bulletin TCB3 entitled *User's Manual for the Installation of Underground Corrugated Coilable Plastic Utilities Duct,* or in accordance with manufacturer's recommendation.

Authorized Engineering Information 3-8-1978.

Copyright National Electrical Manufacturers Association
Provided by IHS under license with NEMA
No reproduction or networking permitted without license from IHS

Not for Resale

# NEMA STANDARDIZATION

The purpose of NEMA Standards, their classification and status are set forth in certain clauses of the NEMA Bylaws, which are quoted below:

## Purpose of Standards

National Electrical Manufacturers Association Standards are adopted in the public interest and are designed to eliminate misunderstandings between the manufacturer and the purchaser and to assist the purchaser in selecting and obtaining the proper product for its particular need. Existence of a National Electrical Manufacturers Association Standard does not in any respect preclude any member or nonmember from manufacturing or selling products not conforming to the standard.

*(Bylaw—Art. V, Sec. 1)*

## Definition of a Standard

A standard of the National Electrical Manufacturers Association defines a product, process or procedure with reference to one or more of the following: nomenclature, composition, construction, dimensions, tolerances, safety, operating characteristics, performance, rating, testing, and the service for which they are designed.

*(Bylaw—Art. V, Sec. 2, Subsection A)*

## Dimensions

Where dimensions are given for interchangeability purposes, alternate dimensions satisfying the other provisions of the standards publication may be capable of otherwise equivalent performance.

*(NEMA Policy Memorandum 84-2, dated June 7, 1984)*

## Classes of Standards

National Electrical Manufacturers Association Standards are of two classes:

1. NEMA Standard, which relates to a product commercially standardized and subject to repetitive manufacture, which standard has been approved by at least 90 percent of the members of the Subdivision eligible to vote thereon;
2. Suggested Standard for Future Design, which may not have been regularly applied to a commercial product, but which suggests a sound engineering approach to future development, which standard has been approved by at least two-thirds of the members of the Subdivision eligible to vote thereon.

*(Bylaw—Art. V, Sec. 2, Subsection B)*

## Authorized Engineering Information

Authorized Engineering Information consists of explanatory data and other engineering information of an informative character not falling within the classification of NEMA Standard or Suggested Standard for Future Design.

*(Bylaw—Art. V, Sec. 6, 1st Sentence)*

## Official Standards Proposal

An Official Standards Proposal is an official draft of a proposed standard which is formally recommended to an outside organization(s) for consideration, comment and/or approval.

*(Bylaw—Art. V, Sec. 4, Subsection A)*

## Identification of Status

Standards in NEMA Standards Publications are identified in the foreword or following each standard as "NEMA Standard" or "Suggested Standard for Future Design." These indicate the status of the standard. These words are followed by a date which indicates when the standard was adopted in its present form by the Association.

The material identified as "Authorized Engineering Information" and "Official Standards Proposal" is designated similarly.

Copyright National Electrical Manufacturers Association
Provided by IHS under license with NEMA
No reproduction or networking permitted without license from IHS
Not for Resale

# PLASTIC CONDUIT, DUCT AND ACCESSORIES SECTION OF THE NATIONAL ELECTRICAL MANUFACTURERS ASSOCIATION

## MEMBER COMPANIES

Can-Tex Industries
Mineral Wells, TX 76067

Carlon, Electrical Sciences, Inc.
Cleveland, OH 44122

Certainteed Corporation
Valley Forge, PA 19482

Challenger Electrical Materials, Inc.
Parkersburg, WV 26101

Formex Manufacturing, Inc.
Atlanta, GA 30362

Hercules Incorporated
Wilmington, DE 19899

Koch Fiberglass Products Company
Wichita, KS 67217

Midwest Plastic Fabricators, Inc.
Chagrin Falls, OH 44022

NVF Company
Fiber Glass Tubular Division
Houston, TX 77038

Robroy Industries, Inc.
Verona, PA 15147

A.O. Smith-Inland, Inc.
Little Rock, AR 72209

Underground Devices, Inc.
Glenview, IL 60025

Underground Products, Inc.
Troy, MI 48099-3230

Copyright National Electrical Manufacturers Association
Provided by IHS under license with NEMA
No reproduction or networking permitted without license from IHS
Not for Resale