NEMA Standards Publication No. WC 52-1985 (R1991) (R2000)

High-Temperature and Electronic Insulated Wire—Impulse Dielectric Testing

Published by:

National Electrical Manufacturers Association
1300 North 17th Street, Suite 1847
Rosslyn, VA 22209

© Copyright 2001 by the National Electrical Manufacturers Association. All rights including translation into other languages, reserved under the Universal Copyright Convention, the Berne Convention for the Protection of Literary and Artistic Works, and the International and Pan American Copyright Conventions.

--`,,`,,`-`-`,,`,,`,`,,`---

Copyright National Electrical Manufacturers Association
Provided by IHS under license with NEMA
No reproduction or networking permitted without license from IHS

Not for Resale

NOTICE AND DISCLAIMER

The information in this publication was considered technically sound by the consensus of persons engaged in the development and approval of the document at the time it was developed. Consensus does not necessarily mean that there is unanimous agreement among every person participating in the development of this document.

The National Electrical Manufacturers Association (NEMA) standards and guideline publications, of which the document contained herein is one, are developed through a voluntary consensus standards development process. This process brings together volunteers and/or seeks out the views of persons who have an interest in the topic covered by this publication. While NEMA administers the process and establishes rules to promote fairness in the development of consensus, it does not write the document and it does not independently test, evaluate, or verify the accuracy or completeness of any information or the soundness of any judgments contained in its standards and guideline publications.

NEMA disclaims liability for any personal injury, property, or other damages of any nature whatsoever, whether special, indirect, consequential, or compensatory, directly or indirectly resulting from the publication, use of, application, or reliance on this document. NEMA disclaims and makes no guaranty or warranty, express or implied, as to the accuracy or completeness of any information published herein, and disclaims and makes no warranty that the information in this document will fulfill any of your particular purposes or needs. NEMA does not undertake to guarantee the performance of any individual manufacturer or seller's products or services by virtue of this standard or guide.

In publishing and making this document available, NEMA is not undertaking to render professional or other services for or on behalf of any person or entity, nor is NEMA undertaking to perform any duty owed by any person or entity to someone else. Anyone using this document should rely on his or her own independent judgment or, as appropriate, seek the advice of a competent professional in determining the exercise of reasonable care in any given circumstances. Information and other standards on the topic covered by this publication may be available from other sources, which the user may wish to consult for additional views or information not covered by this publication.

NEMA has no power, nor does it undertake to police or enforce compliance with the contents of this document. NEMA does not certify, test, or inspect products, designs, or installations for safety or health purposes. Any certification or other statement of compliance with any health or safety–related information in this document shall not be attributable to NEMA and is solely the responsibility of the certifier or maker of the statement.

Copyright National Electrical Manufacturers Association
Provided by IHS under license with NEMA
No reproduction or networking permitted without license from IHS
Not for Resale

To: Current Holders of WC 52-1985 (R1991)
From: NEMA Communications Department
Date: October 4, 2001
Subject: Reaffirmation of WC 52-1985 (R1991)

Setting Standards for Excellence

The NEMA Codes and Standards Committee has reaffirmed WC 52-1985 (R1991), "High Temperature and Electronic Insulated Wire—Impulse Dielectric Testing."

The new designator for this standard is: WC 52-1985 (R1991) (R2000), "High Temperature and Electronic Insulated Wire—Impulse Dielectric Testing."

Please insert the attached revised title page into your standard.

Copyright National Electrical Manufacturers Association
Provided by IHS under license with NEMA
No reproduction or networking permitted without license from IHS
Not for Resale

ADOPTION NOTICE

National Electrical Manufacturers Association (NEMA) Standard NEMA WC 52, "*High Temperature and Electronic Insulated Wire-Impulse Dielectric Testing*", was adopted on 11 August 2000 for use by the Department of Defense (DoD). Proposed changes by DoD activities must be submitted to the DoD Adopting Activity: Defense Logistics Agency, Defense Supply Center, Columbus, ATTN: DSCC-VAI, P.O. Box 3990, Columbus, OH 43216-5000. DoD activities may obtain copies of this standard from the Document Automation and Production Service, Building 4/D, 700 Robbins Avenue, Philadelphia, PA 19111-5094. The private sector and other Government agencies may purchase the document from the National Electrical Manufacturers Association, 1300 North 17th Street, Suite 1847, Rosslyn, VA 22209.

CONCLUDING MATERIAL

Custodians:
Navy - SH
Air Force - 11
DLA - CC

Adopting Activity:
DLA - CC

(Project 6145-2258)

Review activity:
Navy - AS

DISTRIBUTION STATEMENT A. Approved for public release; distribution is unlimited.

Copyright National Electrical Manufacturers Association
Provided by IHS under license with NEMA
No reproduction or networking permitted without license from IHS
Not for Resale

WC 52-85 6470247 0005358 3
A-33-13
A-33-01

NEMA STANDARDS PUBLICATION/NO. WC 52

nema

High-Temperature and Electronic Insulated Wire —Impulse Dielectric Testing

NEMA

NATIONAL ELECTRICAL MANUFACTURERS ASSOCIATION ■ 2101 L STREET, N.W., WASHINGTON, D.C. 20037

Copyright National Electrical Manufacturers Association
Provided by IHS under license with NEMA
No reproduction or networking permitted without license from IHS
Not for Resale

TABLE OF CONTENTS

		Page
	FOREWORD	i
	SCOPE	ii
Section 1	TEST EQUIPMENT	
	Electrode	1
	Wave Form	1
	Voltmeter	1
	Capacitive Regulation	1
	Failure Detection Circuit	1
Section 2	TEST PROCEDURE	
	Set-Up	2
	Fault Identification	2
	Calibration	2
	Operation of Test Voltage Generator (Quick Check Method)	2
Appendix	TEST VOLTAGES	3

Copyright National Electrical Manufacturers Association
Provided by IHS under license with NEMA
No reproduction or networking permitted without license from IHS
Not for Resale

WC 52

HIGH TEMPERATURE AND ELECTRONIC INSULATED WIRE—IMPULSE DIELECTRIC TESTING

Published by

National Electrical Manufacturers Association
2101 L Street, NW
Washington, DC 20037
(202) 457-8400

© 1986 by National Electrical Manufacturers Association

Copyright National Electrical Manufacturers Association
Provided by IHS under license with NEMA
No reproduction or networking permitted without license from IHS
Not for Resale

Foreword

This Standards Publication was developed as an advancement over sparktesting at an industrial frequency followed by wet dielectric testing. Impulse dielectric testing embodies the benefits of testing under impulse conditions, the positive presence of corona on the surface of the wire for uniform stress distribution, and the sensitivity of modern electronic circuitry at relatively low power levels.

Initially an annular ring electrode was utilized by industry; later on it was found that a high density bead chain will provide more consistent results by reducing the effects of different ionizing conditions due to varying humidity or temperature in the testing environment.

A large number of NEMA companies was involved in the development of this Standards Publication. Very good correlation of test results was achieved over a period of 2½ years. This Standard now is referenced in many military and commercial specifications. It is recognized as a significant tool to reduce the possibility of creating conductor corrosion due to the presence of water beneath the insulation.

Publication No. WC 52-1985 revises and supersedes the NEMA Standards Publication No. HP 1-1979, *High Temperature Insulated Wire—Impulse Dielectric Testing*. User needs have been considered throughout the development of these standards.

These standards are periodically reviewed by the High Temperature Insulated Wire and Cable Section and the Electronic Wire and Cable Section of NEMA for any revisions necessary to keep them up to date with advancing technology. Proposed or recommended revisions should be submitted to:

Manager, Engineer Department
National Electrical Manufacturers Association
2101 L Street, NW
Washington, DC 20037

Copyright National Electrical Manufacturers Association
Provided by IHS under license with NEMA
No reproduction or networking permitted without license from IHS
Not for Resale

Scope

This procedure is intended for the dielectric testing of insulation of unshielded single-conductor wires. This procedure is not intended for use with multi-conductor cable.

Copyright National Electrical Manufacturers Association
Provided by IHS under license with NEMA
No reproduction or networking permitted without license from IHS
Not for Resale

HIGH-TEMPERATURE AND ELECTRONIC INSULATED WIRE—IMPULSE DIELECTRIC TESTING

Section 1

TEST EQUIPMENT

1.1 ELECTRODE

The electrode shall be of a bead chain construction that will give intimate metallic contact with practically all of the wire insulation surface. The electrode length shall be chosen so that, at the speed being used, the wire will be subjected to no less than 3 nor more than 100 pulses at any given cross section.

NEMA Standard 11-14-1985.

1.1.1 Wave Form

The wave form of the voltage applied to the electrode shall consist of a negative pulse followed by a damped oscillation. The negative pulse shall have a maximum 0 to 90 percent rise time of 75 microseconds. The repetition rate shall be between 200 and 250 pulses per second. The specified voltage shall be defined as the peak magnitude of the initial negative pulse. The peak value of the first positive overshoot and each of the following damped oscillations shall be smaller than the initial negative pulse. The wave form shall be analyzed to determine how long each pulse and the following damped oscillations (both positive and negative) remain at an absolute potential of 80 percent or greater of the initial negative peak. This time duration shall be between 20 and 100 microseconds. The dampening shall be such that the oscillations will be reduced to less than 1 percent of the peak voltage before the next pulse starts. The wave form measurement shall be made without the use of a coupling capacitor.

The peak and root means square (rms) voltages shall be measured with a wire of typical design located in the electrode and its conductor grounded.

NEMA Standard 11-14-1985.

1.2 VOLTMETER

A voltmeter measuring the peak voltage of the initial negative pulse at the electrode shall continually indicate the electrode potential. The full-scale meter reading shall be not greater than 15 peak kV. The meter accuracy shall be such that, when the voltage is adjusted to any specified value as measured by the instrument voltmeter, the actual electrode value will be within ± 4 percent of the indicated voltage.

NEMA Standard 11-14-1985.

1.2.1 Capacitive Regulation

The indicated voltage shall decrease no more than 12 percent when a capacitive load connected between the electrode and ground is increased from an initial value of 12.5 to 25 picofarads per inch of electrode length.

NEMA Standard 11-14-1985.

1.3 FAILURE DETECTION CIRCUIT

There shall be a fault-indicating circuit which will give a visible or audible indication of a dielectric failure so that the wire can be stopped or suitably identified. The system shall be sufficiently sensitive so that a fault can be detected at 75 percent of the selected test voltage when the electrode is arced to ground through a 20,000-ohm resistance. The unit shall also be capable of detecting a fault which lasts for the duration of only one impulse.

NEMA Standard 11-14-1985.

Copyright National Electrical Manufacturers Association
Provided by IHS under license with NEMA
No reproduction or networking permitted without license from IHS
Not for Resale

Section 2

TEST PROCEDURE

2.1 SET-UP

The insulated wire shall be threaded through the electrode head and the conductor grounded at one or both ends. With the electrode head energized to the specified voltage (see the Appendix for typical test voltages), the wire shall pass from the payoff spool through the electrode and on to the take-up spool. The voltage shall be adjusted with the wire in the electrode.

NEMA Standard 11-14-1985.

2.1.1 Fault Identification

If any dielectric failures occur, they shall be cut out or suitably identified for subsequent removal, along with at least 2 inches of wire on each side of the fault. The equipment shall be so wired as to automatically deenergize the high voltage when the wire is stopped. During the string-up of a new length, every attempt shall be made to expose the entire length, including ends, to the specified voltage. Any ends not tested shall be clearly marked and removed subsequent to this test.

NEMA Standard 11-14-1985.

2.2 CALIBRATION

The instrument voltmeter and wave form shall be checked for compliance with these standards at each intended operating voltage by means of a calibrated oscilloscope connected to the bead electrode in conjunction with a suitable compensated attenuator. The peak magnitude of the initial negative pulse, the 0 to 90 percent rise time (first transition duration), the pulse duration at and above the 80 percent peak, the pulse repetition rate, and the capacitive regulation shall all be derived from the wave form display. All devices used for calibration shall have traceability to the National Bureau of Standards.

NEMA Standard 11-14-1985.

2.3 OPERATION OF TEST VOLTAGE GENERATOR (QUICK CHECK METHOD)

As a quick means to check the normal operation of the test voltage generator, the peak and rms voltages may be measured (using an electrostatic voltmeter with and without peak detecting attachment). The ratio of these voltages should be within 4.5 and 5.5 to 1. If not, careful calibration of the instrument voltmeter with particular attention to the wave shape of the voltage is recommended.

Authorized Engineering Information 11-14-1985.

Copyright National Electrical Manufacturers Association
Provided by IHS under license with NEMA
No reproduction or networking permitted without license from IHS

Not for Resale

Appendix

TEST VOLTAGES

Military Specification Designation		Bead Chain Voltage Settings kV Peak
MIL-W-16878	/1A	8.0
	/2A	10.0
	/3A	12.0
	/4	6.5
	/5	8.0
	/6	4.0
	/7	6.5
	/8	8.0
	/10B	8.0
	/11	6.5
	/12	8.0
	/13	4.0
	/14	8.0
	/15	10.0
	/16	12.0
	/17	8.0
	/18	10.0
	/19	12.0
	/20	4.0
	/21	6.5
	/22	8.0
	/23	4.0
	/24	4.0
	/25	6.5
	/26	6.5
	/27	8.0
	/28	8.0
	/29	6.5
	/30	10.0
	/31	10.0
	/32	8.0
	/33	8.0
	/34	8.0
	/35	8.0
MIL-W-22759	/1	6.5
	/2	6.5
	/3	8.0
	/4	8.0
	/5	8.0
	/6	8.0
	/7	8.0
	/8	8.0
	/9	9.5
	/10	9.5
	/11	8.0 (6.5 for #16AWG & larger gauges of wire)*
	/12	8.0 (6.5 for #16AWG & larger gauges of wire)*
	/13	8.0
	/14	8.0
	/15	8.0
	/16	8.0
	/17	8.0
	/18	8.0
	/19	8.0
	/20	9.5
	/21	9.5
	/22	8.0
	/23	8.0
	/28	8.0
	/29	8.0
	/30	8.0
	/31	8.0
	/32	8.0
	/33	8.0
	/34	8.0
	/35	8.0
	/41	8.0
	/42	8.0
	/43	8.0
MIL-W-81044	/6	8.0
	/7	8.0
	/9	8.0
	/10	8.0
	/12	8.0
	/13	8.0
MIL-W-81381	/7	8.0
	/8	8.0
	/9	8.0
	/10	8.0
	/11	8.0
	/12	8.0
	/13	8.0
	/14	8.0
	/17	8.0
	/18	8.0
	/19	8.0
	/21	8.0
	/22	8.0
MIL-W-5086	/1A	8.0
	/2B	8.0
	/3A	8.0
	/4A	13.0
	/5B	8.0
	/6B	8.0
	/7A	8.0
	/8A	8.0

*with the military specification designation.

Copyright National Electrical Manufacturers Association
Provided by IHS under license with NEMA
No reproduction or networking permitted without license from IHS
Not for Resale

September 1984

NEMA STANDARDIZATION

The purpose of NEMA Standards, their classification and status are set forth in certain clauses of the NEMA Bylaws, which are quoted below:

Purpose of Standards

National Electrical Manufacturers Association Standards are adopted in the public interest and are designed to eliminate misunderstandings between the manufacturer and the purchaser and to assist the purchaser in selecting and obtaining the proper product for its particular need. Existence of a National Electrical Manufacturers Association Standard does not in any respect preclude any member or nonmember from manufacturing or selling products not conforming to the standard.

(Bylaw—Art. V, Sec. 1)

Definition of a Standard

A standard of the National Electrical Manufacturers Association defines a product, process or procedure with reference to one or more of the following: nomenclature, composition, construction, dimensions, tolerances, safety, operating characteristics, performance, rating, testing, and the service for which they are designed.

(Bylaw—Art. V, Sec. 2, Subsection A)

Dimensions

Where dimensions are given for interchangeability purposes, alternate dimensions satisfying the other provisions of the standards publication may be capable of otherwise equivalent performance.

(NEMA Policy Memorandum 84-2, dated June 7, 1984)

Classes of Standards

National Electrical Manufacturers Association Standards are of two classes:

1. NEMA Standard, which relates to a product commercially standardized and subject to repetitive manufacture, which standard has been approved by at least 90 percent of the members of the Subdivision eligible to vote thereon;
2. Suggested Standard for Future Design, which may not have been regularly applied to a commercial product, but which suggests a sound engineering approach to future development, which standard has been approved by at least two-thirds of the members of the Subdivision eligible to vote thereon.

(Bylaw—Art. V, Sec. 2, Subsection B)

Authorized Engineering Information

Authorized Engineering Information consists of explanatory data and other engineering information of an informative character not falling within the classification of NEMA Standard or Suggested Standard for Future Design.

(Bylaw—Art. V, Sec. 6, 1st Sentence)

Official Standards Proposal

An Official Standards Proposal is an official draft of a proposed standard which is formally recommended to an outside organization(s) for consideration, comment and/or approval.

(Bylaw—Art. V, Sec. 4, Subsection A)

Identification of Status

Standards in NEMA Standards Publications are identified in the foreword or following each standard as "NEMA Standard" or "Suggested Standard for Future Design." These indicate the status of the standard. These words are followed by a date which indicates when the standard was adopted in its present form by the Association.

The material identified as "Authorized Engineering Information" and "Official Standards Proposal" is similarly.

Copyright National Electrical Manufacturers Association
Provided by IHS under license with NEMA
No reproduction or networking permitted without license from IHS
Not for Resale

ELECTRONIC WIRE AND CABLE SECTION OF THE NATIONAL ELECTRICAL MANUFACTURERS ASSOCIATION

MEMBER COMPANIES

Alpha Wire Corporation
Elizabeth, NJ 07207

Bendix Wire Division
Allied Automative
Farmington Hills, MI 48018

Cable USA, Inc.
Naples, FL 33942

Carol Cable Company, Inc.
Pawtucket, RI 02862

Champlain Cable Corporation
Winooski, VT 05404

Chicago Magnet Wire Corporation
Elk Grove Village, IL 60007

Eaton Corporation
Industrial Polymer Products Division
Aurora, OH 44202

Continental Wire and Cable
Ericsson, Inc.
York, PA 17405

Essex Group, Inc.
Fort Wayne, IN 46801

General Electric Company
Wire and Cable Department
Bridgeport, CT 06602

General Cable Company
Greenwich, CT 06836

Kris-Tech Wire Company, Inc.
Rome, NY 13440

Newcon Wire and Cable Corporation
New Haven, CT 06511

The Okonite Company
Ramsey, NJ 07446

Pacific Electricord Company
Gardena, CA 90247

Philadelphia Insulated Wire Co.
Moorestown, NJ 08057

Pirelli Cable Corporation
Greenwood, SC 31500

Surprenant
Division of F.L. Industries, Inc.
Clinton, MA 01510

Teledyne Thermatics
Elm City, NC 27822

Thermo Electric Company, Inc.
Saddle Brook, NJ 07662

Triangle PWC Inc.
Subs. of Triangle Industries, Inc.
New Brunswick, NJ 08903

Wirekraft
Division of Bristol Corporation
Rolling Prairie, IN 46371

Copyright National Electrical Manufacturers Association
Provided by IHS under license with NEMA
No reproduction or networking permitted without license from IHS
Not for Resale

HIGH TEMPERATURE INSULATED WIRE AND CABLE SECTION OF THE NATIONAL ELECTRICAL MANUFACTURERS ASSOCIATION

MEMBER COMPANIES

Alpha Wire Corporation
Elizabeth, NJ 07207

Barcel Wire and Cable Corp.
Electronics Division
Irvine, CA 92714-5885

Belden Electrical Wire Products
Division of Cooper Industries
Geneva, IL 60134

Bendix Wire Division
Allied Automative
Farmington Hills, MI 48018

Cable USA, Inc.
Naples, FL 33942

Champlain Cable Corporation
Winooski, VT 05404

Continental Wire and Cable
Ericsson, Inc.
York, PA 17405

Eaton Corporation
Industrial Polymer Products Div.
Aurora, OH 44202

General Electric Company
Wire and Cable Department
Bridgeport, CT 06602

Habia/NEK Cable, Inc.
Ronkonkoma, NY 11779

Harbour Industries, Inc.
Shelburne, VT 05482

Hitemp Wires
A Unit of Ericsson, Inc.
Bohemia, NY 11716

The Kerite Company
Subsidiary of Harvey Hubbell, Inc.
Seymour, CT 06483

Independent Cable, Inc.
Hudson, MA 01749

Micro-Tek Corporation
Cinnaminson, NJ 08077

Newcon Wire and Cable Corporation
New Haven, CT 06511

The Okonite Company
Ramsey, NJ 07446

Philadelphia Insulated Wire Company
Moorestown, NJ 08057

Pirelli Cable Corporation
Special Cable Division
Union, NJ 07083

Quirk Wire Company, Inc.
DBA Wirecraft Products
West Brookfield, MA 01585

Radix Wire Company
Cleveland, OH 44132

The Rockbestos Company
New Haven, CT 06504

Siecor
Charlotte, NC 28217

Surprenant Wire and Cable
Division of F.L. Industries, Inc.
Clinton, MA 01510

Teledyne Thermatics
Elm City, NC 27822

Thermo Electric Company, Inc.
Saddle Brook, NJ 07662

Thermax Wire Corporation
Flushing, NY 11354-2897

Times Fiber Communications, Inc.
Wallingford, CT 06492

Wirekraft
Division of Bristol Corporation
Rolling Prairie, IN 46371

Copyright National Electrical Manufacturers Association
Provided by IHS under license with NEMA
No reproduction or networking permitted without license from IHS
Not for Resale